



Pressure-sensitive adhesives   Acrylic   Film

# 2 MIL RAINBOW SEAMLESS POLYESTER / TS523 @ 1.5 Cwt. / 8 PT TAG L-3

ITEM #82389

### Facestock

A 2 mil holographic PET film that can be used for a very wide range of label applications because of its excellent mechanical and chemical properties, as well as its dimensional stability. The print surface is top coated to improve printability.

**Type**  
Film

**Tensile MD**  
23 Lbs/in

**Tensile CD**  
23 Lbs/in

**Elong MD**  
118

**Elong CD**  
118

**Properties**

**Value**

**Caliper**

2.00 Mil

### Regulatory Approval

**RoHS**  
Yes

**Prop65**  
Yes

**REACH**  
Yes

**TPCH**  
Yes

**CPSIA**  
Yes

**UL**  
No

**FSC**  
No

\*Please contact your sales representative for details

### Adhesive

A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.

**Composition**  
Acrylic

**Type**  
Permanent

**Shear**  
300

**Application Temperature**  
35 F

**Min. Application Temperature**  
-65 F

**Max. Application Temperature**  
180 F

**Properties**

**Value**

<b>Stainless Steel</b>	5.2 lbs/linear in.	
<b>Glass</b>	2.8	
<b>Polyethylene</b>	2.9	
<b>Corrugated</b>	1.40 lbs./in.	
<b>Painted Metal</b>	5.2 lbs/linear in.	
<b>Loop Tack</b>	2.20 lbs./in2	
<b>Regulatory Approval</b>		
<b>RoHS</b> Yes	<b>Prop65</b> No	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>UL</b> No
<b>Direct Food</b> No	<b>Indirect Food</b> Yes	
*Please contact your sales representative for details		

<b>Liner</b> An 8pt, 100# tag liner which has been silicone coated one side to give a controlled release. It has exceptionally high internal strength to withstand all conventional processing operations including die-cutting, perforating, fanfolding and refolding processes.		
<b>Type</b> 17380		
<b>Tensile MD</b> 63 Lbs/In	<b>Tensile CD</b> 34 Lbs/In	
<b>Tear MD</b> 149 Grams	<b>Tear CD</b> 156 Grams	
<b>Description</b>	<b>Value</b>	
<b>Basis Weight</b>	102 Lbs/Rm	
<b>Caliper</b>	8.0 Mil	
<b>Regulatory Approval</b>		
<b>RoHS</b> Yes	<b>Prop65</b> Yes	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>UL</b> No
<b>Direct Food</b> No		
*Please contact your sales representative for details		

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

222 Mound Avenue Miamisburg, OH 45342

[800-358-4448](tel:800-358-4448)

[orders.us@beontag.com](mailto:orders.us@beontag.com)