

2 MIL TC METALLIZED BOPP / TR440 @ 1.0 Cwt. / 40#SCK L-3

ITEM #1458

Facestock

A 2 mil coated one side metallized BOPP designed for high sheen, metallized appearance and high-speed press performance. Typical applications are beverage, health and beauty and pharmaceutical. Outstanding water based flexo, UV flexo, UV letterpress and rotary screen ink adhesion.

Type

Film

Tensile MD

137.5 PSI

Tensile CD

241 PSI

Elong MD

180

Elong CD

55

Properties

Value

Caliper

2.0

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

FSC

No

*Please contact your sales representative for details

Adhesive

A specialty clear acrylic adhesive showing good initial removable tack with high shear and high removable adhesion. This adhesive has excellent clarity & minimum cold flow. Good removability on a wide range of substrates including corrugated and many plastic surfaces.

Composition

Acrylic

Type

Removable

Shear

110

Application Temperature

40 F

Min. Application Temperature

-65 F

Max. Application Temperature

150 F

Properties

Value

Stainless Steel

4.7 lbs/linear in.

Glass	3.0	
Polyethylene	1.4	
Corrugated	1.20 lbs./in.	
Painted Metal	4.2 lbs/linear in.	
Loop Tack	1.70 lbs./in.	
Regulatory Approval		
RoHS Yes	Prop65 No	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No	Indirect Food Yes	
*Please contact your sales representative for details		

Liner Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.		
Type 5517342		
Tensile MD 34 Lbs/In	Tensile CD 22 Lbs/In	
Tear MD 32 Grams	Tear CD 34 Grams	
Description	Value	
Basis Weight	40 Lbs/Rm	
Caliper	2.5 Mil	
Regulatory Approval		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No		
*Please contact your sales representative for details		

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

222 Mound Avenue Miamisburg, OH 45342

[800-358-4448](tel:800-358-4448)

orders.us@beontag.com