

2.3 mil Polar White BOPP / TS523 @ 1.5 Cwt. / 40#SCK L-3

ITEM #95294

Facestock

A 2.3 mil white BOPP with a 50% gloss level. Outstanding whiteness and opacity. Topcoated for printability using standard print methods and thermal transfer (with resin ribbon only). This film has high machine direction stiffness and tensile strength for superior high speed label dispensing.

Type

Film

Tensile MD

20000 Psi

Tensile CD

35000 Psi

Elong MD

180

Elong CD

60

Properties

Value

Caliper

2.30 Mil

Opacity

89

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

UL

No

FSC

No

*Please contact your sales representative for details

Adhesive

A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.

Composition

Acrylic

Type

Permanent

Shear

300

Application Temperature

35 F

Min. Application Temperature

-65 F

Max. Application Temperature

180 F

| Properties | Value |
|-----------------|---------------------------|
| Stainless Steel | 5.2 lbs/linear in. |
| Glass | 2.8 |
| Polyethylene | 2.9 |
| Corrugated | 1.40 lbs./in. |
| Painted Metal | 5.2 lbs/linear in. |
| Loop Tack | 2.20 lbs./in ² |

| Regulatory Approval | | |
|---------------------|---------------|-------|
| RoHS | Prop65 | REACH |
| Yes | No | Yes |
| TPCH | CPSIA | UL |
| Yes | Yes | No |
| Direct Food | Indirect Food | |
| No | Yes | |

*Please contact your sales representative for details

| Liner | | |
|---|------------|-------|
| Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing. | | |
| Type | | |
| 5517342 | | |
| Tensile MD | Tensile CD | |
| 34 Lbs/In | 22 Lbs/In | |
| Tear MD | Tear CD | |
| 32 Grams | 34 Grams | |
| Description | Value | |
| Basis Weight | 40 Lbs/Rm | |
| Caliper | 2.5 Mil | |
| Regulatory Approval | | |
| RoHS | Prop65 | REACH |
| Yes | Yes | Yes |
| TPCH | CPSIA | UL |
| Yes | Yes | No |
| Direct Food | | |
| No | | |
| *Please contact your sales representative for details | | |

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

222 Mound Avenue Miamisburg, OH 45342

[800-358-4448](tel:800-358-4448)

orders.us@beontag.com