



Pressure-sensitive adhesives

Hot Melt

Film

# 2.6 MIL LABEL LYTE / AP151 @ 1.3 Cwt. / 40#SCK L-3

ITEM #151271

### Facestock

A 2.6 mil heat set, biaxially oriented multi-layer white polypropylene film. It is designed for excellent opacity and has a high surface treatment for good ink adhesion while maintaining it's pearlescent look.

#### Type

Film

#### Tensile MD

13000 Psi

#### Tensile CD

25000 Psi

#### Elong MD

100

#### Elong CD

50

Properties	Value
Caliper	2.60 Mil
Opacity	88

### Regulatory Approval

#### FSC

No

\*Please contact your sales representative for details

### Adhesive

An improved general purpose permanent rubber based adhesive which has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting & stripping traits.

Type	Composition	Shear
Permanent	Hot Melt	80
Application Temperature	Min. Application Temperature	Max. Application Temperature
35 F	-65 F	220 F

Properties	Value
Stainless Steel	7.3 lbs/linear in.
Glass	5.7
Polyethylene	6.5

<b>Corrugated</b>	2.50 lbs./in.	
<b>Painted Metal</b>	7.0 lbs/linear in.	
<b>Loop Tack</b>	5.00 lbs./in.	

---

<b>Regulatory Approval</b>		
<b>RoHS</b>	<b>Prop65</b>	<b>REACH</b>
Yes	No	Yes
<b>TPCH</b>	<b>CPSIA</b>	<b>UL</b>
Yes	Yes	No
<b>Direct Food</b>	<b>Indirect Food</b>	
No	Yes	

\*Please contact your sales representative for details

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type

5517342

Tensile MD

34 Lbs/In

Tensile CD

22 Lbs/In

Tear MD

32 Grams

Tear CD

34 Grams

Description

Value

Basis Weight

40 Lbs/Rm

Caliper

2.5 Mil

Regulatory Approval

RoHS

Yes

TPCH

Yes

Direct Food

No

Prop65

Yes

CPSIA

Yes

REACH

Yes

UL

No

\*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages. BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at

BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

6206 Wolf Creek Pike

Trotwood, OH 45426

[800-358-4448](tel:800-358-4448)

[orders.us@beontag.com](mailto:orders.us@beontag.com)