

Pressure-sensitive adhesives

Acrylic Film

2.6 Mil TechniSheen White BOPP / AT333 @ 1.30 Cwt. / 40#SCK L-3

ITEM #9974346

Facestock

A 2.6 mil biaxially oriented polypropylene with a cavitated opaque OPP core and a top-coated glossy print surface. Suitable for a wide variety of pressure sensitive label applications.

Type Film		
Tensile MD 13000 Psi	Tensile CD 20000 Psi	
Elong MD 120	Elong CD 45	
Properties	Value	
Caliper	2.60 Mil	
Regulatory Approval		
RoHS	Prop65	REACH
Yes	Yes	Yes
ТРСН	CPSIA	FSC
Yes	Yes	No
*Please contact your sales representative for details		

Adhesive

An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 F. Very good plasticizer, UV and solvent resistance. AT333 adhesive allows for short term reposition on many substrates, yet displays excellent permanency at room temps.

Composition Acrylic	Type Permanent	Shear 60
Application Temperature -20 F	Min. Application Temperature -65 F	Max. Application Temperature 160 F
Properties	Value	
Stainless Steel	4.7 lbs/linear in.	

Polyethylene	2.2	
Corrugated	1.40 lbs./in.	
Painted Metal	4.4 lbs/linear in.	
Loop Tack	2.20 lbs./in.	
Regulatory Approval		
RoHS	Prop65	REACH
	Prop65 No	REACH Yes
RoHS	-	

Direct Food	Indirect Food
No	Yes

*Please contact your sales representative for details

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type 5517342			
Tensile MD	Tensile CD		
34 Lbs/In	22 Lbs/In		
Tear MD	Tear CD		
32 Grams	34 Grams		
Description	Value		
Basis Weight	40 Lbs/Rm		
Caliper	2.5 Mil		
Regulatory Approval			
RoHS	Prop65	REACH	
Yes	Yes	Yes	

TPCH Yes	CPSIA Yes
Direct Food No	
*Please contact your sales representative for c	letails

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

UL

No

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag 222 Mound Avenue Miamisburg, OH 45342 <u>800-358-4448</u> orders.us@beontag.com