

2.6 MIL TECHNISHEEN WHITE BOPP / TS523 @ 1.5 Cwt.
/ 40#SCK L-3

ITEM #9974345

<

| | | |
|---|--|--|
| Adhesive A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive. | | |
| | | |
| Type Permanent | Composition Acrylic | Shear 300 |
| Application Temperature 35 F | Min. Application Temperature -65 F | Max. Application Temperature 180 F |
| | | |
| Properties | Value | |
| Stainless Steel | 5.2 lbs/linear in. | |
| Glass | 2.8 | |

| | | |
|---|-----------------------------|---------------------|
| Polyethylene | 2.9 | |
| Corrugated | 1.40 lbs./in. | |
| Painted Metal | 5.2 lbs/linear in. | |
| Loop Tack | 2.20 lbs./in2 | |
| Regulatory Approval | | |
| RoHS Yes | Prop65 No | REACH Yes |
| TPCH Yes | CPSIA Yes | UL No |
| Direct Food No | Indirect Food Yes | |
| *Please contact your sales representative for details | | |

| | | |
|---|--------------------------------|---------------------|
| Liner Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing. | | |
| Type 5517342 | | |
| Tensile MD 34 Lbs/In | Tensile CD 22 Lbs/In | |
| Tear MD 32 Grams | Tear CD 34 Grams | |
| Description Value | | |
| Basis Weight | 40 Lbs/Rm | |
| Caliper | 2.5 Mil | |
| Regulatory Approval | | |
| RoHS Yes | Prop65 Yes | REACH Yes |
| TPCH Yes | CPSIA Yes | UL No |
| Direct Food No | | |
| *Please contact your sales representative for details | | |

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

6206 Wolf Creek Pike

Trotwood, OH 45426

[800-358-4448](tel:800-358-4448)

orders.us@beontag.com