

Pressure-sensitive adhesives

Acrylic Film

2.6 MIL WHITE TT BOPP / AT333 @ 1.30 Cwt. / 40#SCK L-3 TU

ITEM #86620

A 2.6 Mil matte white polypropylene film that is designed for thermal transfer printability. Features good weather resistance and dimensional stability.

Туре			
Film			
Tensile MD	Tensile CD		
13800	26800		
Elong MD	Elong CD		
170	55		
Properties	Value		
Caliper	2.6 mil		
canper	2.0		
Regulatory Approval			
RoHS	Prop65	REACH	
Yes	Yes	Yes	
	100		
ТРСН	CPSIA	FSC	
Yes	Yes	No	
*Please contact your sales repr	esentative for details		

Adhesive

An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 F. Very good plasticizer, UV and solvent resistance. AT333 adhesive allows for short term reposition on many substrates, yet displays excellent permanency at room temps.

Composition Acrylic	Type Permanent	Shear 60
Application Temperature -20 F	Min. Application Temperature -65 F	Max. Application Temperature 160 F
Properties	Value	
Stainless Steel	4.7 lbs/linear in.	

Polyethylene	2.2	
Corrugated	1.40 lbs./in.	
Painted Metal	4.4 lbs/linear in.	
Loop Tack	2.20 lbs./in.	
Regulatory Approval		
RoHS	Prop65	REACH
Yes	No	Yes
ТРСН	CPSIA	UL
Yes	Yes	No
Direct Food	Indirect Food	

*Please contact your sales representative for details

Yes

Liner

No

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. Technicote Ultimate silicone release coating provides consistent stripping at high converting speeds through a flat release profile. This paper has a smooth, caliper consistent surface and withstands all conventional processing operations.

Туре 718322			
Tensile MD 30 Lbs/in	Tensile CD 20 Lbs/In		
Tear MD 32 Grams	Tear CD 34 Grams		
Description	Value		
Basis Weight	40 Lbs/Rm		
Caliper	2.5 Mil		
Regulatory Approval			
RoHS	Prop65	REACH	
Yes	Yes	Yes	

TPCH Yes	CPSIA Yes
Direct Food No	
*Please contact your sales representative for c	letails

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

UL

No

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag 222 Mound Avenue Miamisburg, OH 45342 <u>800-358-4448</u> orders.us@beontag.com