

2.6 MIL WHITE TT BOPP / TR440 @ 1.0 Cwt. / 3.4 MIL LAYFLAT L-3

ITEM #86708

Facestock

A 2.6 Mil matte white polypropylene film that is designed for thermal transfer printability. Features good weather resistance and dimensional stability.

Type		
Film		
Tensile MD	Tensile CD	
13800	26800	
Elong MD	Elong CD	
170	55	

Properties	Value
Caliper	2.6 mil

Regulatory Approval

RoHS	Prop65	REACH
Yes	Yes	Yes
TPCH	CPSIA	FSC
Yes	Yes	No

*Please contact your sales representative for details

<div><div>Adhesive</div><div>A specialty clear acrylic adhesive showing good initial removable tack with high shear and high removable adhesion. This adhesive has excellent clarity & minimum cold flow. Good removability on a wide range of substrates including corrugated and many plastic surfaces.</div></div>		
<div><div>Type</div><div>Removable</div></div>	<div><div>Composition</div><div>Acrylic</div></div>	<div><div>Shear</div><div>110</div></div>
<div><div>Application Temperature</div><div>40 F</div></div>	<div><div>Min. Application Temperature</div><div>-65 F</div></div>	<div><div>Max. Application Temperature</div><div>150 F</div></div>
<div><div>Properties</div><div>Value</div></div>		
<div><div>Stainless Steel</div></div>	<div><div>4.7 lbs/linear in.</div></div>	
<div><div>Glass</div></div>	<div><div>3.0</div></div>	

Polyethylene	1.4	
Corrugated	1.20 lbs./in.	
Painted Metal	4.2 lbs/linear in.	
Loop Tack	1.70 lbs./in.	
Regulatory Approval		
RoHS Yes	Prop65 No	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No	Indirect Food Yes	
*Please contact your sales representative for details		

Liner A bleached kraft liner which has been silicone coated one side to give a controlled release. It is designed to withstand die-cutting, marginal punching, perforating, fanfolding and refolding process while providing excellent dimensional stability.		
Tensile MD 35	Tensile CD 15	
Tear MD 50	Tear CD 75	
Description		
Value		
Basis Weight	0	
Caliper	3,4	
Regulatory Approval		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	
*Please contact your sales representative for details		

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages. BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag

6206 Wolf Creek Pike
Trotwood, OH 45426
[800-358-4448](tel:800-358-4448)
orders.us@beontag.com