

Pressure-sensitive adhesives

Acrylic

Film

# 2.6 MIL WHITE TT BOPP / TR440 @ 1.0 Cwt. / 40#SCK L-3

ITEM #86640

#### **Facestock**

A 2.6 Mil matte white polypropylene film that is designed for thermal transfer printability. Features good weather resistance and dimensional stability.

#### **Type**

Film

 Tensile MD
 Tensile CD

 13800
 26800

 Elong MD
 Elong CD

 170
 55

Properties Value

**Caliper** 2.6 mil

# **Regulatory Approval**

RoHS<br/>YesProp65<br/>YesREACH<br/>YesTPCH<br/>YesCPSIA<br/>YesFSC<br/>No

## **Adhesive**

A specialty clear acrylic adhesive showing good initial removable tack with high shear and high removable adhesion. This adhesive has excellent clarity & minimum cold flow. Good removability on a wide range of substrates including corrugated and many plastic surfaces.

<b>Composition</b> Acrylic	<b>Type</b> Removable	<b>Shear</b> 110
<b>Application Temperature</b> 40 F	<b>Min. Application Temperature</b> -65 F	<b>Max. Application Temperature</b> 150 F
Properties	Value	
Stainless Steel	4.7 lbs/linear in.	
Glass	3.0	

<sup>\*</sup>Please contact your sales representative for details

Polyethylene 1.4

Corrugated 1.20 lbs./in.

Painted Metal 4.2 lbs/linear in.

**Loop Tack** 1.70 lbs./in.

## **Regulatory Approval**

RoHSProp65REACHYesNoYesTPCHCPSIAULYesYesNo

Direct Food Indirect Food

No Yes

#### Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

#### Туре

5517342

Tensile MDTensile CD34 Lbs/In22 Lbs/In

**Tear MD**32 Grams

Tear CD
34 Grams

Description Value

Basis Weight 40 Lbs/Rm

Caliper 2.5 Mil

## **Regulatory Approval**

RoHSProp65REACHYesYesYes
TPCH
CPSIA
Yes
No

**Direct Food** 

No

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

<sup>\*</sup>Please contact your sales representative for details

<sup>\*</sup>Please contact your sales representative for details

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
222 Mound Avenue Miamisburg, OH 45342
800-358-4448
orders.us@beontag.com