

Pressure-sensitive adhesives

Hot Melt

Film

# 2.7 MIL TC LABEL LYTE / TP500 / 50#SCK L-3

ITEM #74352

#### **Facestock**

A white, opaque multi-layer cavitated polypropylene film that has been designed for rigid and semi-rigid pressure sensitive applications that require excellent opacity and durability as well as exceptional graphic appeal. Coated two sides for outstanding ink and adhesive anchorage.

Film

Tensile MDTensile CD13000 Psi27400 Psi

**Elong MD**200
50

Properties Value

Caliper 2.70 Mil

# **Regulatory Approval**

RoHS<br/>YesProp65<br/>YesREACH<br/>YesTPCH<br/>YesCPSIA<br/>YesFSC<br/>No

## **Adhesive**

A general purpose hotmelt adhesive with high initial tack and excellent ultimate adhesion. This adhesive demonstrates good resistance to water, UV, solvent and plasticizer. TP500 has outstanding adhesion to most plastic substrates, especially HDPE milk jugs.

<b>Type</b> Permanent	<b>Composition</b> Hot Melt	<b>Shear</b> 50
<b>Application Temperature</b> 25 F	<b>Min. Application Temperature</b> -65 F	<b>Max. Application Temperature</b> 140 F
Properties	Value	
Stainless Steel	6.2 lbs/linear in.	
Glass	3.5	

<sup>\*</sup>Please contact your sales representative for details

Polyethylene 4.7

Corrugated 1.50 lbs./in.

Painted Metal 4.0 lbs/linear in.

Loop Tack 3.50 lbs./in.

## **Regulatory Approval**

RoHSProp65REACHYesNoYesTPCHCPSIAUL

Yes Yes No

Direct Food Indirect Food

No Yes

#### Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

## Туре

5517353

Tensile MDTensile CD40 Lbs/In24 Lbs/In

**Tear MD**44 Grams
48 Grams

Description Value

Basis Weight 50 Lbs/Rm

Caliper 3.2 Mil

## **Regulatory Approval**

RoHSProp65REACHYesYesYes
TPCH
CPSIA
Yes
No

#### **Direct Food**

No

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

<sup>\*</sup>Please contact your sales representative for details

<sup>\*</sup>Please contact your sales representative for details

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
800-358-4448
orders.us@beontag.com