

# 2.7 MIL TC LABEL LYTE / TR440 @ 1.0 Cwt. / 40#SCK L-3

ITEM #74336

### Facestock

A white, opaque multi-layer cavitated polypropylene film that has been designed for rigid and semi-rigid pressure sensitive applications that require excellent opacity and durability as well as exceptional graphic appeal. Coated two sides for outstanding ink and adhesive anchorage.

#### Type

Film

#### Tensile MD

13000 Psi

#### Tensile CD

27400 Psi

#### Elong MD

200

#### Elong CD

50

Properties	Value
------------	-------

Caliper	2.70 Mil
---------	----------

### Regulatory Approval

RoHS	Prop65	REACH
------	--------	-------

Yes	Yes	Yes
-----	-----	-----

TPCH	CPSIA	FSC
------	-------	-----

Yes	Yes	No
-----	-----	----

\*Please contact your sales representative for details

### Adhesive

A specialty clear acrylic adhesive showing good initial removable tack with high shear and high removable adhesion. This adhesive has excellent clarity & minimum cold flow. Good removability on a wide range of substrates including corrugated and many plastic surfaces.

Type	Composition	Shear
------	-------------	-------

Removable	Acrylic	110
-----------	---------	-----

Application Temperature	Min. Application Temperature	Max. Application Temperature
-------------------------	------------------------------	------------------------------

40 F	-65 F	150 F
------	-------	-------

Properties	Value
------------	-------

Stainless Steel	4.7 lbs/linear in.
-----------------	--------------------

<b>Glass</b>	3.0	
<b>Polyethylene</b>	1.4	
<b>Corrugated</b>	1.20 lbs./in.	
<b>Painted Metal</b>	4.2 lbs/linear in.	
<b>Loop Tack</b>	1.70 lbs./in.	
<b>Regulatory Approval</b>		
<b>RoHS</b> Yes	<b>Prop65</b> No	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>UL</b> No
<b>Direct Food</b> No	<b>Indirect Food</b> Yes	
*Please contact your sales representative for details		

<b>Liner</b> Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.		
<b>Type</b> 5517342		
<b>Tensile MD</b> 34 Lbs/In	<b>Tensile CD</b> 22 Lbs/In	
<b>Tear MD</b> 32 Grams	<b>Tear CD</b> 34 Grams	
<b>Description</b>	<b>Value</b>	
<b>Basis Weight</b>	40 Lbs/Rm	
<b>Caliper</b>	2.5 Mil	
<b>Regulatory Approval</b>		
<b>RoHS</b> Yes	<b>Prop65</b> Yes	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>UL</b> No
<b>Direct Food</b> No		
*Please contact your sales representative for details		

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

6206 Wolf Creek Pike

Trotwood, OH 45426

[800-358-4448](tel:800-358-4448)

[orders.us@beontag.com](mailto:orders.us@beontag.com)