

Pressure-sensitive adhesives

Acrylic Film

2.7 MIL TC LABEL LYTE / TS523 HCWT / 50#SCK L-3

ITEM #74335

Facestock

A white, opaque multi-layer cavitated polypropylene film that has been designed for rigid and semi-rigid pressure sensitive applications that require excellent opacity and durability as well as exceptional graphic appeal. Coated two sides for outstanding ink and adhesive anchorage.

Type Film		
Tensile MD 13000 Psi	Tensile CD 27400 Psi	
Elong MD 200	Elong CD 50	
Properties	Value	
Caliper	2.70 Mil	
Regulatory Approval		
RoHS	Prop65	REACH
Yes	Yes	Yes
ТРСН	CPSIA	FSC
Yes	Yes	No
*Please contact your sales representative fo	r details	

Adhesive

A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.

Composition Acrylic	Type Permanent	Shear 350
Application Temperature 35 F	Min. Application Temperature -65 F	Max. Application Temperature 180 F
Properties	Value	
Stainless Steel	5.2 lbs/linear in.	
Glass	2.8	

Polyethylene	2.9		
Corrugated	1.40 lbs./in.		
Painted Metal	5.2 lbs/linear in.		
Loop Tack	2.20 lbs./in2		
Regulatory Approval			
RoHS	Prop65	REACH	
RoHS Yes	Prop65 No	REACH Yes	
	-		
Yes	No	Yes	
Yes TPCH	No	Yes UL	
Yes TPCH Yes	No CPSIA Yes	Yes UL	

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type 5517353			
Tensile MD	Tensile CD		
40 Lbs/In	24 Lbs/In		
Tear MD	Tear CD		
44 Grams	48 Grams		
Description	Value		
Basis Weight	50 Lbs/Rm		
Caliper	3.2 Mil		
Regulatory Approval			
RoHS	Prop65	REACH	
Yes	Yes	Yes	
ТРСН	CPSIA	UL	

ТРСН	CPSIA	UL	
Yes	Yes	No	
Direct Food No			
*Please contact your sales repre	sentative for details		

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag 222 Mound Avenue Miamisburg, OH 45342 <u>800-358-4448</u> orders.us@beontag.com