

3.0 MIL POLYART / AT150 @ 1.3 Cwt. / 40#SCK L-3

ITEM #66575

Facestock

A high performance polyethylene base synthetic paper with a unique computer printable top coating allowing Polyart to be printed with flexo, litho, gravure, letterpress and screen methods. It can also be used with thermal transfer, ion dep, dot matrix and certain ink jets.

Type

Film

Tensile MD

5800 Psi

Tensile CD

5510 Psi

Elong MD

130

Elong CD

110

Properties	Value
Caliper	3.00 Mil
Opacity	90

Regulatory Approval

RoHS	Prop65	REACH
Yes	Yes	Yes
TPCH	CPSIA	FSC
Yes	Yes	No

*Please contact your sales representative for details

Adhesive

An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 °F. Very good plasticizer, UV and solvent resistance. AT150 adhesive allows for short term reposition on many substrates, yet displays excellent permanency at room temps

Composition	Type	Shear
Acrylic	Permanent	100
Application Temperature	Min. Application Temperature	Max. Application Temperature
-20 F	-65 F	160 F

Typical Adhesion values

Properties	Value
Stainless Steel	5.1 lbs/linear in.

Glass	4.0
Polyethylene	4.0
Corrugated	1.50 lbs./in.
Painted Metal	4.9 lbs/linear in.
Loop Tack	2.90 lbs./in.

Regulatory Approval

RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	Direct Food No
Indirect Food Yes		

*Please contact your sales representative for details

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type
5517342

Tensile MD
34 Lbs/In

Tensile CD
22 Lbs/In

Tear MD
32 Grams

Tensile CD
34 Grams

Description	Value
Basis Weight	40 Lbs/Rm
Caliper	2.5 Mil

Regulatory Approval

RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No		

*Please contact your sales representative for details

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

222 Mound Avenue Miamisburg, OH 45342

[800-358-4448](tel:800-358-4448)

orders.us@beontag.com