

Pressure-sensitive adhesives

Acrylic

Film

# 3.0 MIL POLYART / AT333 @ 1.30 Cwt. / 40#SCK L-3

ITEM #66550

#### **Facestock**

A high performance polyethylene base synthetic paper with a unique computer printable top coating allowing Polyart to be printed with flexo, litho, gravure, letterpress and screen methods. It can also be used with thermal transfer, ion dep, dot matrix and certain ink jets.

T	уp	•

Film

Tensile MD
5800 Psi
5510 Psi

Elong MD
Elong CD
130
110

Properties	Value
Caliper	3.00 Mil
Opacity	90

## **Regulatory Approval**

RoHS	Prop65	REACH
Yes	Yes	Yes
TPCH	CPSIA	FSC
Yes	Yes	No

<sup>\*</sup>Please contact your sales representative for details

### **Adhesive**

An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 F. Very good plasticizer, UV and solvent resistance. AT333 adhesive allows for short term reposition on many substrates, yet displays excellent permanency at room temps.

<b>Composition</b> Acrylic	<b>Type</b> Permanent	<b>Shear</b> 60
<b>Application Temperature</b> -20 F	<b>Min. Application Temperature</b> -65 F	<b>Max. Application Temperature</b> 160 F
Properties	Value	
Stainless Steel	4.7 lbs/linear in.	

**Glass** 1.3

Polyethylene 2.2

Corrugated 1.40 lbs./in.

Painted Metal 4.4 lbs/linear in.

**Loop Tack** 2.20 lbs./in.

# **Regulatory Approval**

RoHSProp65REACHYesNoYesTPCHCPSIAUL

Yes

Direct Food Indirect Food

No Yes

#### Liner

Yes

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

No

## Туре

5517342

Tensile MD

34 Lbs/ln

22 Lbs/ln

Tear MD

Tear CD

Tear MDTear CD32 Grams34 Grams

**Description** Value

**Basis Weight** 40 Lbs/Rm

**Caliper** 2.5 Mil

# **Regulatory Approval**

RoHS<br/>YesProp65<br/>YesREACH<br/>YesTPCH<br/>YesCPSIA<br/>YesUL<br/>No

## **Direct Food**

No

Last update: 05/01/2024

<sup>\*</sup>Please contact your sales representative for details

<sup>\*</sup>Please contact your sales representative for details

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS: Beontag 222 Mound Avenue Miamisburg, OH 45342

800-358-4448 orders.us@beontag.com