

Pressure-sensitive adhesives

Hot Melt

Film

# 3.6 MIL POLYART / AP151 @ 1.3 Cwt. GRAY OPAQUE / 50#SCK L-3

ITEM #6800

#### **Facestock**

A high performance polyethylene base synthetic paper with a unique computer printable top coating allowing Polyart to be printed with flexo, litho, gravure, letterpress and screen methods. It can also be used with thermal transfer, ion dep and dot matrix.

# Type

Film

Tensile MD
6670 Psi
5510 Psi

Tear MD
496 Grams
599 Grams

Elong MD Elong CD 120 110

Properties Value

Caliper 3.60 Mil

Opacity 90

# **Regulatory Approval**

RoHS	Prop65	REACH
Yes	Yes	Yes
TPCH	CPSIA	FSC
11 011	OI OIA	100
Yes	Yes	No

<sup>\*</sup>Please contact your sales representative for details

#### **Adhesive**

An improved general purpose permanent rubber based adhesive which has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting & stripping traits.

Composition Hot Melt	<b>Type</b> Permanent	<b>Shear</b> 80
<b>Application Temperature</b> 35 F	<b>Min. Application Temperature</b> -65 F	<b>Max. Application Temperature</b> 220 F

Properties	Value		
Stainless Steel	7.3 lbs/linear in.		
Glass	5.7		
Polyethylene	6.5		
Corrugated	2.50 lbs./in.		
Painted Metal	7.0 lbs/linear in.		
Loop Tack	5.00 lbs./in.		
Regulatory Approval			
RoHS	Prop65	REACH	
Yes	No	Yes	
ТРСН	CPSIA	UL	

No

Direct Food Indirect Food

Yes

No Yes

### Liner

Yes

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

# Type

5517353

Tensile MD

40 Lbs/ln

24 Lbs/ln

Tear MD

44 Grams

48 Grams

Description	Value
Basis Weight	50 Lbs/Rm
Caliper	3.2 Mil

# **Regulatory Approval**

RoHS	Prop65	REACH
Yes	Yes	Yes
ТРСН	CPSIA	UL
Yes	Yes	No

#### **Direct Food**

No

<sup>\*</sup>Please contact your sales representative for details

<sup>\*</sup>Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
222 Mound Avenue Miamisburg, OH 45342
800-358-4448
orders.us@beontag.com