

3.7 MIL SMUDGE KIMDURA / TR447 @ 1.4 Cwt. / 50#SCK L-3

ITEM #4788

Facestock

A 3.7 mil white Smudge Kimdura which is a biaxially oriented three ply polypropylene which combines extraordinary edge tear resistance with a smooth, uniform surface that provides brilliant imagery, superior print quality and smudge resistance.

Type
Film

Tensile MD
24 Lbs/in

Tensile CD
18 Lbs/in

Tear MD
26 Grams

Tear CD
15 Grams

| Properties | Value |
|------------|-------|
|------------|-------|

| | |
|---------|----------|
| Caliper | 3.70 Mil |
|---------|----------|

Regulatory Approval

| | | |
|--------------------|----------------------|---------------------|
| RoHS Yes | Prop65 Yes | REACH Yes |
| TPCH Yes | CPSIA Yes | FSC No |

*Please contact your sales representative for details

Adhesive

A general purpose, removable rubber based emulsion adhesive featuring good initial tack and moderate adhesion. It has limited plasticizer, UV and solvent resistance. This is a standard removable adhesive for tape reels, computer disks and kids stickers.

| | | |
|--|--|--|
| Type Removable | Composition Hot Melt | Shear 40 |
| Application Temperature 40 F | Min. Application Temperature 1 F | Max. Application Temperature 120 F |

| Properties | Value |
|------------|-------|
|------------|-------|

| | |
|-----------------|--------------------|
| Stainless Steel | 2.5 lbs/linear in. |
|-----------------|--------------------|

| | | |
|---|-----------------------------|---------------------|
| Glass | 0.9 | |
| Polyethylene | 1.8 | |
| Corrugated | 1.00 lbs./in. | |
| Painted Metal | 1.6 lbs/linear in. | |
| Loop Tack | 1.50 lbs./in. | |
| Regulatory Approval | | |
| RoHS Yes | Prop65 No | REACH Yes |
| TPCH Yes | CPSIA Yes | UL No |
| Direct Food No | Indirect Food Yes | |
| *Please contact your sales representative for details | | |

| | | |
|---|--------------------------------|---------------------|
| Liner Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing. | | |
| Type 5517353 | | |
| Tensile MD 40 Lbs/In | Tensile CD 24 Lbs/In | |
| Tear MD 44 Grams | Tear CD 48 Grams | |
| Description | Value | |
| Basis Weight | 50 Lbs/Rm | |
| Caliper | 3.2 Mil | |
| Regulatory Approval | | |
| RoHS Yes | Prop65 Yes | REACH Yes |
| TPCH Yes | CPSIA Yes | UL No |
| Direct Food No | | |
| *Please contact your sales representative for details | | |

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

6206 Wolf Creek Pike

Trotwood, OH 45426

[800-358-4448](tel:800-358-4448)

orders.us@beontag.com