



Pressure-sensitive adhesives

Hot Melt

Film

4 MIL FLEXIBLE TC VINYL / TL250 @ 2.5 Cwt. / 50#SCK L-3

ITEM #4279

Facestock

A 4 mil flexible white vinyl with polymeric plasticizers, formulated to provide optimum performance with pressure sensitive adhesives. The top-coating provides outstanding adhesion to various printing inks.

Type
Film

Tensile MD
3900 lb/in

Tensile CD
3800 lb/in

Tear MD
100 Grams

Tear CD
100 Grams

Properties	Value
------------	-------

Caliper	4.0
---------	-----

Regulatory Approval

RoHS
Yes

Prop65
Yes

REACH
Yes

TPCH
Yes

CPSIA
Yes

FSC
No

*Please contact your sales representative for details

Adhesive

An outstanding general purpose permanent adhesive which has high initial tack and high ultimate adhesion. It is used for tire label and many other difficult to label substrates.

Type
Permanent

Composition
Hot Melt

Shear
80

Application Temperature
35 F

Min. Application Temperature
-65 F

Max. Application Temperature
220 F

Properties	Value
------------	-------

Stainless Steel	8.3 lbs/linear in.
-----------------	--------------------

Glass	6.7
-------	-----

Polyethylene	7.5	
Corrugated	2.90 lbs./in.	
Painted Metal	8.0 lbs/linear in.	
Loop Tack	5.40 lbs./in2	
Regulatory Approval		
RoHS Yes	Prop65 No	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No	Indirect Food Yes	FDA 21 CFR 175.105, BfR XIV No
*Please contact your sales representative for details		

Liner Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.		
Type 5517353		
Tensile MD 40 Lbs/In	Tensile CD 24 Lbs/In	
Tear MD 44 Grams	Tear CD 48 Grams	
Description		
Value		
Basis Weight	50 Lbs/Rm	
Caliper	3.2 Mil	
Regulatory Approval		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No		
*Please contact your sales representative for details		

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

6206 Wolf Creek Pike

Trotwood, OH 45426

[800-358-4448](tel:800-358-4448)

orders.us@beontag.com