

# 4 MIL FLEXIBLE TC VINYL / TR440 / 65# FBK L-10

ITEM #6172

**Facestock**

A 4 mil flexible white vinyl with polymeric plasticizers, formulated to provide optimum performance with pressure sensitive adhesives. The top-coating provides outstanding adhesion to various printing inks.

<b>Type</b> Film		
<b>Tensile MD</b> 3900 lb/in	<b>Tensile CD</b> 3800 lb/in	
<b>Tear MD</b> 100 Grams	<b>Tear CD</b> 100 Grams	

Properties	Value
Caliper	4.0

**Regulatory Approval**

<b>RoHS</b> Yes	<b>Prop65</b> Yes	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>FSC</b> No

\*Please contact your sales representative for details

**Adhesive**

A specialty clear acrylic adhesive showing good initial removable tack with high shear and high removable adhesion. This adhesive has excellent clarity & minimum cold flow. Good removability on a wide range of substrates including corrugated and many plastic surfaces.

<b>Composition</b> Acrylic	<b>Type</b> Removable	<b>Shear</b> 110
<b>Application Temperature</b> 40 F	<b>Min. Application Temperature</b> -65 F	<b>Max. Application Temperature</b> 150 F

Properties	Value
Stainless Steel	4.7 lbs/linear in.
Glass	3.0
Polyethylene	1.4

<b>Corrugated</b>	1.20 lbs./in.	
<b>Painted Metal</b>	4.2 lbs/linear in.	
<b>Loop Tack</b>	1.70 lbs./in.	

---

<b>Regulatory Approval</b>		
<b>RoHS</b>	<b>Prop65</b>	<b>REACH</b>
Yes	No	Yes
<b>TPCH</b>	<b>CPSIA</b>	<b>UL</b>
Yes	Yes	No
<b>Direct Food</b>	<b>Indirect Food</b>	
No	Yes	

\*Please contact your sales representative for details

Liner

A fully bleached kraft liner which has been silicone coated one side to give a controlled release. This paper has high internal strength to withstand all conventional processing operations including die-cutting, perforating, fanfolding and refolding processes.

Tensile MD	Tensile CD
33	18
Tear MD	Tear CD
51	53

Description	Value
Basis Weight	0
Caliper	3,8

Regulatory Approval

RoHS	Prop65	REACH
Yes	Yes	Yes
TPCH	CPSIA	
Yes	Yes	

\*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages. BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:  
Beontag  
222 Mound Avenue Miamisburg, OH 45342  
[800-358-4448](tel:800-358-4448)

