

# 4 WHITE DIRECT THERMAL BOPP / TP800 / 40#SCK L-3

ITEM #233082

## Facestock

Facestock (4.0 mil White DT BOPP): A white direct thermal top coated, biaxially oriented (BOPP) film that may be used in a wide variety of pressure sensitive label applications. The white polypropylene is treated one side with a print receptive coating for superb ink adhesion, and has great stiffness for efficient dispensability.

**Type**  
Film

<b>Tensile MD</b> 7,000	<b>Tensile CD</b> 19,000 lbs/i
----------------------------	-----------------------------------

<b>Elong MD</b> 220	<b>Elong CD</b> 38
------------------------	-----------------------

Properties	Value
------------	-------

<b>Caliper</b>	4.0 mil
----------------	---------

## Regulatory Approval

<b>RoHS</b> Yes	<b>Prop65</b> Yes	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>UL</b> No
<b>FSC</b> No		

\*Please contact your sales representative for details

## Adhesive

TP800 is a high performance all-temp hot melt adhesive with quick initial tack and outstanding adhesion to common packaging films at subzero temperatures.

<b>Composition</b> Hot Melt	<b>Type</b> Permanant
--------------------------------	--------------------------

Properties	Value
------------	-------

<b>Glass</b>	3.4
--------------	-----

<b>Polyethylene</b>	4.8
---------------------	-----

<b>Regulatory Approval</b>		
<b>RoHS</b> Yes	<b>Prop65</b> Yes	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>UL</b> No
<b>Direct Food</b> No	<b>Indirect Food</b> Yes	
*Please contact your sales representative for details		

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type

5517342

Tensile MD

34 Lbs/In

Tensile CD

22 Lbs/In

Tear MD

32 Grams

Tear CD

34 Grams

Description

Value

Basis Weight

40 Lbs/Rm

Caliper

2.5 Mil

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

UL

No

Direct Food

No

\*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages. BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:  
Beontag  
222 Mound Avenue Miamisburg, OH 45342

[800-358-4448](tel:800-358-4448)  
[orders.us@beontag.com](mailto:orders.us@beontag.com)