

50# BRIGHT WHITE EDP / TP170 @ 1.3 Cwt. / 40#SCK
L-3

ITEM #4406998

Facestock

This is a high brightness, surface-sized free sheet. Its smoothness and optical properties are designed to yield clean, crisp printed images. Its physical properties provide the dimensional stability and strength required in the pressure sensitive label converting process.

Type

Paper

Tensile MD

30 Lbs/in

Tensile CD

15 Lbs/in

Tear MD

40 Grams

Tear CD

50 Grams

Properties

Value

Caliper

3.50 Mil

Opacity

90

Brightness

92

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

FSC

No

*Please contact your sales representative for details

Adhesive

A general purpose acrylic adhesive showing good initial tack with high shear and high ultimate adhesion. It has good plasticizer, UV and solvent resistance. This adhesive displays excellent die-cutting and stripping characteristics and has good adhesion to many different substrates.

Type

Permanent

Composition

Acrylic

Shear

300

Application Temperature

35 F

Min. Application Temperature

-65 F

Max. Application Temperature

180 F

| Properties | Value |
|-----------------|--------------------|
| Stainless Steel | 5.2 lbs/linear in. |
| Glass | 3.2 |
| Polyethylene | 1.6 |
| Corrugated | 1.40 lbs./in. |
| Painted Metal | 5.2 lbs/linear |
| Loop Tack | 2.20 lbs./in2 |

Regulatory Approval

| | | |
|-------------|---------------|-------|
| RoHS | Prop65 | REACH |
| Yes | No | Yes |
| TPCH | CPSIA | UL |
| Yes | Yes | No |
| Direct Food | Indirect Food | |
| No | Yes | |

*Please contact your sales representative for details

Adhesive

A general purpose patterned acrylic adhesive showing good initial tack with high shear and high ultimate adhesion. It has good plasticizer, UV and solvent resistance. This adhesive displays excellent die-cutting and stripping characteristics and has good adhesion to many different substrates.

| | | |
|-------------------------|------------------------------|------------------------------|
| Type | Composition | Shear |
| Permanent | Acrylic | 300 |
| Application Temperature | Min. Application Temperature | Max. Application Temperature |
| 35 F | -65 F | 180 F |

| Properties | Value |
|-----------------|--------------------|
| Stainless Steel | 5.2 lbs/linear in. |
| Glass | 3.2 |
| Polyethylene | 1.6 |
| Corrugated | 1.40 lbs./in. |
| Painted Metal | 5.2 lbs/linear |
| Loop Tack | 2.20 lbs./in2 |

Regulatory Approval

| | | |
|-------------|---------------|-------|
| RoHS | Prop65 | REACH |
| Yes | No | Yes |
| TPCH | CPSIA | UL |
| Yes | Yes | No |
| Direct Food | Indirect Food | |

| | |
|---|-----|
| No | Yes |
| *Please contact your sales representative for details | |

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type

5517342

Tensile MD

34 Lbs/In

Tensile CD

22 Lbs/In

Tear MD

32 Grams

Tear CD

34 Grams

Description

Value

Basis Weight

40 Lbs/Rm

Caliper

2.5 Mil

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

UL

No

Direct Food

No

*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
[800-358-4448](tel:800-358-4448)
orders.us@beontag.com