

Pressure-sensitive adhesives

Hot Melt

Paper

# 50# BROWN KRAFT / AP151 @ 1.3 Cwt. / 40#SCK L-3

ITEM #151033

#### **Facestock**

This unbleached brown kraft is smudge resistant, has excellent ink receptivity (inks should be designed to avoid excessive absorption) and is designed for high speed converting. It has excellent perforating, punching and fanfolding characteristics.

## Type

Paper

Tensile MD

35 Lbs/in

23 Lbs/in

Tear MD

Tear CD

116 Grams

132 Grams

Properties Value

Caliper 5.50 Mil

## **Regulatory Approval**

RoHSProp65REACHYesYesYes
TPCH
CPSIA
FSC
Yes
No

#### **Adhesive**

An improved general purpose permanent rubber based adhesive which has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting & stripping traits.

Туре	Composition	Shear
Permanent	Hot Melt	80

Application Temperature Min. Application Temperature Max. Application Temperature

35 F -65 F 220 F

Properties	Value
Stainless Steel	7.3 lbs/linear in.
Glass	5.7

<sup>\*</sup>Please contact your sales representative for details

Polyethylene 6.5

Corrugated 2.50 lbs./in.

Painted Metal 7.0 lbs/linear in.

**Loop Tack** 5.00 lbs./in.

#### **Regulatory Approval**

RoHS<br/>YesProp65<br/>NoREACH<br/>YesTPCHCPSIAUL

Yes

Direct Food Indirect Food

No Yes

#### Liner

Yes

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

No

## Туре

5517342

Tensile MDTensile CD34 Lbs/In22 Lbs/In

Tear MDTear CD32 Grams34 Grams

Description Value

Basis Weight 40 Lbs/Rm

Caliper 2.5 Mil

## **Regulatory Approval**

RoHS<br/>YesProp65<br/>YesREACH<br/>YesTPCH<br/>YesCPSIA<br/>YesUL<br/>No

#### **Direct Food**

No

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

<sup>\*</sup>Please contact your sales representative for details

<sup>\*</sup>Please contact your sales representative for details

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
800-358-4448
orders.us@beontag.com