

50# RADIANT WHITE LASER / TP170 @ 1.3 Cwt. / 3.4 MIL LAYFLAT L-3

ITEM #559582

Facestock	
<div>Type</div> <div>Paper</div>	
<div>Tensile MD</div> <div>34 Lbs/in</div>	<div>Tensile CD</div> <div>22 Lbs/in</div>
<div>Tear MD</div> <div>50 Grams</div>	<div>Tear CD</div> <div>56 Grams</div>
Properties	Value
Caliper	4.00 Mil
Opacity	89
Brightness	94
Regulatory Approval	
<div>FSC</div> <div>No</div>	
*Please contact your sales representative for details	

Adhesive		
A general purpose acrylic adhesive showing good initial tack with high shear and high ultimate adhesion. It has good plasticizer, UV and solvent resistance. This adhesive displays excellent die-cutting and stripping characteristics and has good adhesion to many different substrates.		
<div>Composition</div> <div>Acrylic</div>	<div>Type</div> <div>Permanent</div>	<div>Shear</div> <div>300</div>
<div>Application Temperature</div> <div>35 F</div>	<div>Min. Application Temperature</div> <div>-65 F</div>	<div>Max. Application Temperature</div> <div>180 F</div>
Properties	Value	
Stainless Steel	5.2 lbs/linear in.	
Glass	3.2	

Polyethylene	1.6	
Corrugated	1.40 lbs./in.	
Painted Metal	5.2 lbs/linear	
Loop Tack	2.20 lbs./in2	
Regulatory Approval		
RoHS	Prop65	REACH
Yes	No	Yes
TPCH	CPSIA	UL
Yes	Yes	No
Direct Food	Indirect Food	
No	Yes	
*Please contact your sales representative for details		

Liner		
A bleached kraft liner which has been silicone coated one side to give a controlled release. It is designed to withstand die-cutting, marginal punching, perforating, fanfolding and refolding process while providing excellent dimensional stability.		
Tensile MD	Tensile CD	
35	15	
Tear MD	Tear CD	
50	75	
DescriptionValue		
Basis Weight	0	
Caliper	3,4	
Regulatory Approval		
RoHS	Prop65	REACH
Yes	Yes	Yes
TPCH	CPSIA	
Yes	Yes	
*Please contact your sales representative for details		

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag

222 Mound Avenue Miamisburg, OH 45342
[800-358-4448](tel:800-358-4448)
orders.us@beontag.com