



Pressure-sensitive adhesives

Hot Melt

Paper

# 55# HIBRIGHT SemiGloss / AP151 @ 1.5 CWT / 40#SCK L-2

ITEM #88000

## Facestock

A premium semigloss calendar coated one side stock with excellent ink receptivity and print characteristics. This stock offers an 88% brightness has an 87% opacity and a 70% gloss rating.

### Type

Paper

### Tensile MD

35 Lbs/in

### Tensile CD

16 Lbs/in

### Tear MD

35 Grams

### Tear CD

38 Grams

Properties	Value
Caliper	2.80 Mil
Opacity	87
Brightness	88

## Regulatory Approval

RoHS	Prop65	REACH
Yes	Yes	Yes
TPCH	CPSIA	FSC
Yes	Yes	No

\*Please contact your sales representative for details

## Adhesive

An improved general purpose permanent rubber based adhesive which has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting & stripping traits.

Composition	Type	Shear
Hot Melt	Permanent	80
Application Temperature	Min. Application Temperature	Max. Application Temperature
35 F	-64 F	220 F

Properties	Value
------------	-------

Stainless Steel	7.3 lbs/linear in.	
Glass	5.7	
Polyethylene	6.5	
Corrugated	2.50 lbs./in.	
Painted Metal	7.0 lbs/linear in.	
Loop Tack	5.00 lbs./in.	
<hr/>		
Regulatory Approval		
RoHS	Prop65	REACH
Yes	No	Yes
TPCH	CPSIA	UL
Yes	Yes	No
Direct Food	Indirect Food	
No	Yes	
*Please contact your sales representative for details		

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

<div>Tensile MD</div> <div>34</div>	<div>Tensile CD</div> <div>22</div>
<div>Tear MD</div> <div>32</div>	<div>Tear CD</div> <div>34</div>

Description	Value
Basis Weight	40
Caliper	2,5

Regulatory Approval

<div>RoHS</div> <div>Yes</div>	<div>Prop65</div> <div>Yes</div>	<div>REACH</div> <div>Yes</div>
<div>TPCH</div> <div>Yes</div>	<div>CPSIA</div> <div>Yes</div>	

\*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages. BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at

BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

222 Mound Avenue Miamisburg, OH 45342

[800-358-4448](tel:800-358-4448)

[orders.us@beontag.com](mailto:orders.us@beontag.com)