

55# HIBRIGHT SEMIGLOSS / AP151 OPAQUE @ 1.3 Cwt.  
/ 40#SCK L-3 / AP151 @ 1.3 CWT / 50#SCK L-3

ITEM #951347

Facestock

A premium semigloss calendar coated one side stock with excellent ink receptivity and print characteristics. This stock offers an 88% brightness has an 87% opacity and a 70% gloss rating.

Type

Paper

Tensile MD

35 Lbs/in

Tensile CD

16 Lbs/in

Tear MD

35 Grams

Tear CD

38 Grams

Properties

Value

Caliper

2.80 Mil

Opacity

87

Brightness

88

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

FSC

No

\*Please contact your sales representative for details

Adhesive

An improved general purpose permanent rubber based adhesive which has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting & stripping traits.

Composition

Hot Melt

Type

Permanent

Shear

80

Application Temperature

35 F

Min. Application Temperature

-65 F

Max. Application Temperature

220 F

Properties

Value

|                 |                    |  |
|-----------------|--------------------|--|
| Stainless Steel | 7.3 lbs/linear in. |  |
| Glass           | 5.7                |  |
| Polyethylene    | 6.5                |  |
| Corrugated      | 2.50 lbs./in.      |  |
| Painted Metal   | 7.0 lbs/linear in. |  |
| Loop Tack       | 5.00 lbs./in.      |  |

|                     |               |       |
|---------------------|---------------|-------|
| Regulatory Approval |               |       |
| RoHS                | Prop65        | REACH |
| Yes                 | No            | Yes   |
| TPCH                | CPSIA         | UL    |
| Yes                 | Yes           | No    |
| Direct Food         | Indirect Food |       |
| No                  | Yes           |       |

\*Please contact your sales representative for details

|  |  |  |
|--|--|--|
| <b>Adhesive</b><br>An outstanding general purpose permanent opaque adhesive that has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting and stripping traits. Provides opacity for cover up applications. |  |  |
| <b>Composition</b><br>Hot Melt   | <b>Type</b><br>Permanent                     | <b>Shear</b><br>80                           |
| <b>Application Temperature</b><br>35 F   | <b>Min. Application Temperature</b><br>-65 F | <b>Max. Application Temperature</b><br>220 F |
| <b>Properties</b>  | <b>Value</b>                                 |  |
| <b>Stainless Steel</b>   | 7.3 lbs/linear in.                           |  |
| <b>Glass</b>   | 5.7  |  |
| <b>Polyethylene</b>  | 6.5  |  |
| <b>Corrugated</b>  | 2.50 lbs./in.                                |  |
| <b>Painted Metal</b>   | 7.0 lbs/linear in.                           |  |
| <b>Loop Tack</b>   | 5.00 lbs./in.                                |  |
| <b>Regulatory Approval</b>   |  |  |
| <b>RoHS</b><br>Yes   | <b>Prop65</b><br>No                          | <b>REACH</b><br>Yes                          |
| <b>TPCH</b><br>Yes   | <b>CPSIA</b><br>Yes                          | <b>UL</b><br>No                              |
| <b>Direct Food</b><br>No   | <b>Indirect Food</b><br>Yes                  |  |

\*Please contact your sales representative for details

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type

5517342

Tensile MD

34 Lbs/In

Tensile CD

22 Lbs/In

Tear MD

32 Grams

Tear CD

34 Grams

Description

Value

Basis Weight

40 Lbs/Rm

Caliper

2.5 Mil

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

UL

No

Direct Food

No

\*Please contact your sales representative for details

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type

5517353

Tensile MD

40 Lbs/In

Tensile CD

24 Lbs/In

Tear MD

44 Grams

Tear CD

48 Grams

Description

Value

Basis Weight

50 Lbs/Rm

Caliper

3.2 Mil

**Regulatory Approval**

**RoHS**  
Yes

**Prop65**  
Yes

**REACH**  
Yes

**TPCH**  
Yes

**CPSIA**  
Yes

**UL**  
No

**Direct Food**  
No

\*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:  
Beontag  
222 Mound Avenue Miamisburg, OH 45342  
[800-358-4448](tel:800-358-4448)  
[orders.us@beontag.com](mailto:orders.us@beontag.com)