

Pressure-sensitive adhesives

Acrylic

Paper

55# HIBRIGHT SemiGloss / TP170 @ 1.3 Cwt. / 40#SCK L-3 TU

ITEM #88079

Facestock

A premium semigloss calendar coated one side stock with excellent ink receptivity and print characteristics. This stock offers an 88% brightness has an 87% opacity and a 70% gloss rating.

Type

Paper

Tensile MD

35 Lbs/in

Tensile CD

16 Lbs/in

Tear MD

35 Grams

Tensile CD

38 Grams

Properties

Value

Caliper

2.80 Mil

Opacity

87

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

FSC

No

*Please contact your sales representative for details

Adhesive

A general purpose acrylic adhesive showing good initial tack with high shear and high ultimate adhesion. It has good plasticizer, UV and solvent resistance. This adhesive displays excellent die-cutting and stripping characteristics and has good adhesion to many different substrates.

Composition

Acrylic

Type

Permanent

Shear

300

Application Temperature

35 F

Min. Application Temperature

-65 F

Max. Application Temperature

180 F

Typical Adhesion values

Properties

Value

Stainless Steel	5.2 lbs/linear in.
Glass	3.0
Polyethylene	1.0
Corrugated	1.40 lbs./in.
Painted Metal	5.2 lbs/linear in.
Loop Tack	2.20 lbs./in.

Regulatory Approval

RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	Direct Food No
Indirect Food Yes		

*Please contact your sales representative for details

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. Technicote Ultimate silicone release coating provides consistent stripping at high converting speeds through a flat release profile. This paper has a smooth, caliper consistent surface and withstands all conventional processing operations.

Type

718322

Tensile MD

30 Lbs/in

Tensile CD

20 Lbs/In

Tear MD

32 Grams

Tensile CD

34 Grams

Description

Value

Basis Weight

40 Lbs/Rm

Caliper

2.5 Mil

Regulatory Approval

RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No		

*Please contact your sales representative for details

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

222 Mound Avenue Miamisburg, OH 45342

[800-358-4448](tel:800-358-4448)

orders.us@beontag.com