

55# HIBRIGHT SemiGloss / TP750 @ 1.3 Cwt. / 40#SCK L-3

ITEM #88023

Facestock

A premium semigloss calendar coated one side stock with excellent ink receptivity and print characteristics. This stock offers an 88% brightness has an 87% opacity and a 70% gloss rating.

Type

Paper

Tensile MD

35 Lbs/in

Tensile CD

16 Lbs/in

Tear MD

35 Grams

Tear CD

38 Grams

Properties

Value

Caliper

2.80 Mil

Opacity

87

Brightness

88

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

FSC

No

*Please contact your sales representative for details

Adhesive

A general purpose hotmelt adhesive with high initial tack and excellent ultimate adhesion. This adhesive demonstrates good resistance to water, UV, solvent and plasticizer. This adhesive has excellent die cutting characteristics for high speed, wide web processing. Excellent adhesion to corrugated and plastics.

Composition

Hot Melt

Type

Permanent

Shear

60

Application Temperature

25 F

Min. Application Temperature

-65 F

Max. Application Temperature

140 F

Properties

Value

| | | |
|---|-----------------------------|--|
| Stainless Steel | 3.7 lbs/linear in. | |
| Glass | 2.0 | |
| Polyethylene | 2.5 | |
| Painted Metal | 4.5 lbs/linear in. | |
| Loop Tack | 2.50 lbs./in. | |
| Regulatory Approval | | |
| RoHS Yes | Prop65 No | REACH Yes |
| TPCH Yes | CPSIA Yes | UL No |
| Direct Food No | Indirect Food Yes | FDA 21 CFR 175.105, BfR XIV No |
| *Please contact your sales representative for details | | |

| | | |
|---|--------------------------------|---------------------|
| Liner Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing. | | |
| Type 5517342 | | |
| Tensile MD 34 Lbs/In | Tensile CD 22 Lbs/In | |
| Tear MD 32 Grams | Tear CD 34 Grams | |
| Description | | |
| Value | | |
| Basis Weight | 40 Lbs/Rm | |
| Caliper | 2.5 Mil | |
| Regulatory Approval | | |
| RoHS Yes | Prop65 Yes | REACH Yes |
| TPCH Yes | CPSIA Yes | UL No |
| Direct Food No | | |
| *Please contact your sales representative for details | | |

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

222 Mound Avenue Miamisburg, OH 45342

[800-358-4448](tel:800-358-4448)

orders.us@beontag.com