

Pressure-sensitive adhesives

Acrylic

Paper

#6 WHITE PEARLIZED ESTATE / IP400 @ 1.7 Cwt. / 44#PK L-4

ITEM #78984

Facestock

This wet strength grade paper face stock features a pearlized white coating on the print side which provides a unique, attractive appearance on glass bottles. It is a favorite for wine and specialty beverage Products.

Type

Paper

| Properties | Value |
|------------|----------|
| Caliper | 5.50 Mil |
| Opacity | 94 |

Regulatory Approval

| RoHS | Prop65 | REACH |
|------|--------|-------|
| Yes | Yes | Yes |
| TPCH | CPSIA | FSC |
| Yes | Yes | No |
| res | 100 | INO |

^{*}Please contact your sales representative for details

Adhesive

A specialty adhesive designed to adhere to glass wine bottles with good ultimate adhesion when applied at temperatures as low as +35 F. Excellent permanency at room temperatures. Good plasticizer, UV & solvent resistance. Excellent adhesive for wet strength wine label facestocks when submersed in ice buckets.

| Type Permanent | Composition Acrylic | Shear 80 |
|-------------------------------------|---|--|
| Application Temperature 35 F | Min. Application Temperature -65 F | Max. Application Temperature 200 F |
| Properties | Value | |
| Stainless Steel | 5.5 lbs/linear in. | |
| Glass | 3.2 | |
| Polyethylene | 2.0 | |
| Corrugated | 1.45 lbs./in. | |

Painted Metal 3.0 lbs/linear in.

Loop Tack 5.00 lbs./in.

Regulatory Approval

RoHSProp65REACHYesNoYes

TPCHCPSIAULYesYesNo

Direct Food Indirect Food

No Yes

Liner

A medium weight natural kraft coated 1 side (C1S) with a gloss polyethylene. Silicone coating has been added on the gloss side (C1S) for a controlled release. It has superb smoothness, excellent dimensional stability and exceptional layflat characteristics.

Type

17745

35 Grams

Tensile MD
35 Lbs/ln
13 Lbs/ln
Tear MD
Tear CD

Description Value

Basis Weight 44 Lbs/Rm

Caliper 3.2 Mil

Regulatory Approval

RoHSProp65REACHYesYesYes
TPCH
CPSIA
Yes
No

50 Grams

Direct Food

No

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

^{*}Please contact your sales representative for details

^{*}Please contact your sales representative for details

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
800-358-4448
orders.us@beontag.com