

Pressure-sensitive adhesives

Latex

Paper

# 60# BRIGHT WHITE EDP / AP151 @ 1.3 Cwt. / 80#FBK L-3

ITEM #151919

## Facestock

This white uncoated litho was designed with smudge resistance for high speed converting while still having excellent perforating, punching & fanfolding characteristics. This stock also offers an 88% in brightness & an 84% opacity.

### Type

Paper

## Regulatory Approval

### FSC

No

\*Please contact your sales representative for details

## Adhesive

An improved general purpose permanent rubber based adhesive which has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting & stripping traits.

### Composition

Latex

### Type

Permanent

### Shear

80

### Application Temperature

35 F

### Min. Application Temperature

-65 F

### Max. Application Temperature

220 F

## Typical Adhesion values

### Properties

### Value

**Stainless Steel**

7.3 lbs/linear in.

**Glass**

5.0

**Polyethylene**

6.0

**Corrugated**

2.50 lbs./in.

**Painted Metal**

7.0 lbs/linear in.

**Loop Tack**

5.00 lbs./in.

## Regulatory Approval

RoHS

Prop65

REACH

Yes

Yes

Yes

**TPCH**

**CPSIA**

**Direct Food**

Yes

Yes

No

**Indirect Food**

Yes

\*Please contact your sales representative for details

**Liner**

A fully bleached kraft liner (FBK) which has been silicone coated one side to give a controlled release. It is designed to withstand all die-cutting, marginal punching, perforating, fanfolding and refolding processes. It is an excellent lay-flat liner.

**Tensile MD**

40

**Tensile CD**

21

**Tear MD**

76

**Tensile CD**

84

**Description**

**Value**

**Basis Weight**

0

**Caliper**

4,5

**Regulatory Approval**

**RoHS**

Yes

**Prop65**

Yes

**REACH**

Yes

**TPCH**

Yes

**CPSIA**

Yes

\*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

222 Mound Avenue Miamisburg, OH 45342

[800-358-4448](tel:800-358-4448)

[orders.us@beontag.com](mailto:orders.us@beontag.com)