

Pressure-sensitive adhesives

Acrylic

Paper

60# BRIGHT WHITE EDP / TP170 @ 1.3 Cwt. / 8 PT TAG L-3

ITEM #2319

Facestock

This white uncoated litho was designed with smudge resistance for high speed converting while still having excellent perforating, punching & fanfolding characteristics. This stock also offers an 88% in brightness & an 84% opacity.

Type

Paper

Regulatory Approval

FSC

No

*Please contact your sales representative for details

Adhesive

A general purpose acrylic adhesive showing good initial tack with high shear and high ultimate adhesion. It has good plasticizer, UV and solvent resistance. This adhesive displays excellent die-cutting and stripping characteristics and has good adhesion to many different substrates.

Composition

Acrylic

Type

Permanent

Shear

300

Application Temperature

35 F

Min. Application Temperature

-65 F

Max. Application Temperature

180 F

Typical Adhesion values

Properties

Value

Stainless Steel

5.2 lbs./linear in.

Glass

3.0

Polyethylene

1.0

Corrugated

1.40 lbs./in.

Painted Metal

5.2 lbs./linear in.

Loop Tack

2.20 lbs./in.

Regulatory Approval

RoHS

Prop65

REACH

Yes

Yes

Yes

TPCH

CPSIA

Direct Food

Yes

Yes

No

Indirect Food

Yes

*Please contact your sales representative for details

Liner

An 8pt, 100# tag liner which has been silicone coated one side to give a controlled release. It has exceptionally high internal strength to withstand all conventional processing operations including die-cutting, perforating, fanfolding and refolding processes.

Type

17380

Tensile MD

63 Lbs/In

Tensile CD

34 Lbs/In

Tear MD

149 Grams

Tensile CD

156 Grams

Description

Value

Basis Weight

102 Lbs/Rm

Caliper

8.0 Mil

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

UL

No

Direct Food

No

*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

222 Mound Avenue Miamisburg, OH 45342

[800-358-4448](tel:800-358-4448)

orders.us@beontag.com