

60# MATTE LITHO / AP151 @ 1.3 Cwt. / 40#SCK L-3

ITEM #7297

Facestock

A premium matte litho stock with excellent ink receptivity and print characteristics. It also offers good flexibility and high internal strength for ease in converting. This face comes with a brightness of 84% and an opacity of 93%.

Type

Paper

Tear MD

50 Grams

Tear CD

55 Grams

Properties

Value

Caliper

3.90 Mil

Opacity

93

Brightness

84

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

FSC

No

*Please contact your sales representative for details

Adhesive An improved general purpose permanent rubber based adhesive which has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting & stripping traits.		
Type Permanent	Composition Hot Melt	Shear 80
Application Temperature 35 F	Min. Application Temperature -65 F	Max. Application Temperature 220 F
Properties	Value	
Stainless Steel	7.3 lbs/linear in.	
Glass	5.7	

Polyethylene	6.5	
Corrugated	2.50 lbs./in.	
Painted Metal	7.0 lbs/linear in.	
Loop Tack	5.00 lbs./in.	
Regulatory Approval		
RoHS Yes	Prop65 No	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No	Indirect Food Yes	
*Please contact your sales representative for details		

Liner Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.		
Type 5517342		
Tensile MD 34 Lbs/In	Tensile CD 22 Lbs/In	
Tear MD 32 Grams	Tear CD 34 Grams	
Description Value		
Basis Weight	40 Lbs/Rm	
Caliper	2.5 Mil	
Regulatory Approval		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No		
*Please contact your sales representative for details		

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

6206 Wolf Creek Pike

Trotwood, OH 45426

[800-358-4448](tel:800-358-4448)

orders.us@beontag.com