

60# ULTRA WHITE SemiGloss / TP750 HCWT /
40#SCK L-3



ITEM #73446

Facestock

A premium coated one side stock with outstanding ink receptivity and print characteristics. It also offers good flexibility and high internal strength for ease in converting. This face offers a 90% Brightness and an 88% opacity.

Type

Paper

Tensile MD

35 Lbs/in

Tensile CD

19 Lbs/in

Tear MD

47 Grams

Tear CD

46 Grams

Properties

Value

Caliper

3.20 Mil

Opacity

88

Brightness

90

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

FSC

Yes

*Please contact your sales representative for details

Adhesive

A general purpose hot melt adhesive with high initial tack and excellent ultimate adhesion. This adhesive demonstrates good resistance to water, UV, solvent and plasticizer. This adhesive has excellent die cutting characteristics for high speed, wide web processing. Excellent adhesion to corrugated and plastics.

Composition

Hot Melt

Type

Permanent

Shear

60

Application Temperature

25 F

Min. Application Temperature

-65 F

Max. Application Temperature

140 F

Properties

Value

Stainless Steel	3.7 lbs/linear in.	
Glass	2.0	
Polyethylene	2.5	
Painted Metal	4.5 lbs/linear in.	
Loop Tack	2.50 lbs./in ²	

Regulatory Approval		
RoHS	Prop65	REACH
Yes	No	Yes
TPCH	CPSIA	UL
Yes	Yes	No
Direct Food	Indirect Food	FDA 21 CFR 175.105, BfR XIV
No	Yes	No

*Please contact your sales representative for details

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type

5517342

Tensile MD

34 Lbs/In

Tensile CD

22 Lbs/In

Tear MD

32 Grams

Tear CD

34 Grams

Description

Value

Basis Weight

40 Lbs/Rm

Caliper

2.5 Mil

Regulatory Approval

RoHS

Yes

TPCH

Yes

Direct Food

No

Prop65

Yes

CPSIA

Yes

REACH

Yes

UL

No

*Please contact your sales representative for details

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

222 Mound Avenue Miamisburg, OH 45342

[800-358-4448](tel:800-358-4448)

orders.us@beontag.com