

7 PT C2S LUMBERTUFF / TL250 @ 2.5 Cwt. / 50#SCK  
L-3

ITEM #80116

Facestock

Coated two side Lumbertuff(R) that has a clay coating on both sides for printability, including thermal transfer. Extremely versatile for applications that need strength and good print results.

Type  
Film

Tensile MD  
28 Lbs/in

Tensile CD  
30 Lbs/in

Tear MD  
7 Grams

Tear CD  
6 Grams

Properties

Value

Caliper

7.00 Mil

Opacity

72

Regulatory Approval

RoHS  
Yes

Prop65  
Yes

REACH  
Yes

TPCH  
Yes

CPSIA  
Yes

FSC  
No

\*Please contact your sales representative for details

Adhesive

An outstanding general purpose permanent adhesive which has high initial tack and high ultimate adhesion. It is used for tire label and many other difficult to label substrates.

Composition  
Hot Melt

Type  
Permanent

Shear  
80

Application Temperature  
35 F

Min. Application Temperature  
-65 F

Max. Application Temperature  
220 F

Properties

Value

Stainless Steel

8.3 lbs/linear in.

<b>Glass</b>	6.7	
<b>Polyethylene</b>	7.5	
<b>Corrugated</b>	2.90 lbs./in.	
<b>Painted Metal</b>	8.0 lbs/linear in.	
<b>Loop Tack</b>	5.40 lbs./in <sup>2</sup>	
<b>Regulatory Approval</b>		
<b>RoHS</b> Yes	<b>Prop65</b> No	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>UL</b> No
<b>Direct Food</b> No	<b>Indirect Food</b> Yes	<b>FDA 21 CFR 175.105, BfR XIV</b> No
*Please contact your sales representative for details		

<b>Liner</b> Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.		
<b>Type</b> 5517353		
<b>Tensile MD</b> 40 Lbs/In	<b>Tensile CD</b> 24 Lbs/In	
<b>Tear MD</b> 44 Grams	<b>Tear CD</b> 48 Grams	
<b>Description</b>	<b>Value</b>	
<b>Basis Weight</b>	50 Lbs/Rm	
<b>Caliper</b>	3.2 Mil	
<b>Regulatory Approval</b>		
<b>RoHS</b> Yes	<b>Prop65</b> Yes	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>UL</b> No
<b>Direct Food</b> No		
*Please contact your sales representative for details		

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

222 Mound Avenue Miamisburg, OH 45342

[800-358-4448](tel:800-358-4448)

[orders.us@beontag.com](mailto:orders.us@beontag.com)