

8 PT TAG / IP400 @ 1.7 Cwt. / 40#SCK L-10

ITEM #72354

Facestock

A coated 1 side tag stock with exceptionally high internal strength. It also offers high stiffness to withstand most conventional processing conditions such as die-cutting, perforating, fan-folding, and refolding operations

Type

Paper

Tensile MD

70

Tensile CD

32

Tear MD

130

Tear CD

130

Properties

Value

Caliper

8 mil

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

UL

No

FSC

No

\*Please contact your sales representative for details

Adhesive

A specialty adhesive designed to adhere to glass wine bottles with good ultimate adhesion when applied at temperatures as low as +35 F. Excellent permanency at room temperatures. Good plasticizer, UV & solvent resistance. Excellent adhesive for wet strength wine label facestocks when submersed in ice buckets.

Composition

Acrylic

Type

Permanent

Shear

80

Application Temperature

35 F

Min. Application Temperature

-65 F

Max. Application Temperature

200 F

Properties

Value

Stainless Steel

5.5 lbs/linear in.

<b>Glass</b>	3.2	
<b>Polyethylene</b>	2.0	
<b>Corrugated</b>	1.45 lbs./in.	
<b>Painted Metal</b>	3.0 lbs/linear in.	
<b>Loop Tack</b>	5.00 lbs./in.	
<b>Regulatory Approval</b>		
<b>RoHS</b> Yes	<b>Prop65</b> No	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>UL</b> No
<b>Direct Food</b> No	<b>Indirect Food</b> Yes	
*Please contact your sales representative for details		

<b>Liner</b> Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.		
<b>Type</b> 17142		
<b>Tensile MD</b> 34 Lbs/In	<b>Tensile CD</b> 22 Lbs/In	
<b>Tear MD</b> 32 Grams	<b>Tear CD</b> 34 Grams	
<b>Description</b>	<b>Value</b>	
<b>Basis Weight</b>	40 Lbs/Rm	
<b>Caliper</b>	2.5 Mil	
<b>Regulatory Approval</b>		
<b>RoHS</b> Yes	<b>Prop65</b> Yes	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>UL</b> No
<b>Direct Food</b> No		
*Please contact your sales representative for details		

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

222 Mound Avenue Miamisburg, OH 45342

[800-358-4448](tel:800-358-4448)

[orders.us@beontag.com](mailto:orders.us@beontag.com)