

Pressure-sensitive adhesives

Acrylic

Paper

8 Pt Tag / TP170 @ 1.30 Cwt. / 40#SCK L-3

ITEM #1132

Facestock

A coated 1 side tag stock with exceptionally high internal strength. It also offers high stiffness to withstand most conventional processing conditions such as die-cutting, perforating, fan-folding, and refolding operations

Туре

Paper

Tensile MD

32

70

130

02

Tensile CD

Tear MD

Tear CD

Properties

Value

Caliper

8 mil

Regulatory Approval

RoHSProp65REACHYesYesYes
TPCH
CPSIA
Yes
No

FSC

No

Adhesive

A general purpose acrylic adhesive showing good initial tack with high shear and high ultimate adhesion. It has good plasticizer, UV and solvent resistance. This adhesive displays excellent die-cutting and stripping characteristics and has good adhesion to many different substrates.

Composition Acrylic	Type Permanent	Shear 300
Application Temperature 35 F	Min. Application Temperature -65 F	Max. Application Temperature 180 F
Properties	Value	
Stainless Steel	5.2 lbs/linear in.	

^{*}Please contact your sales representative for details

Glass 3.2

Polyethylene 1.6

Corrugated 1.40 lbs./in.

Painted Metal 5.2 lbs/linear

Loop Tack 2.20 lbs./in2

Regulatory Approval

RoHS
YesProp65
NoREACH
YesTPCHCPSIAUL

Yes

Direct Food Indirect Food

No Yes

Liner

Yes

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

No

Туре

5517342

Tensile MD

34 Lbs/ln

Tear MD

Tensile CD

22 Lbs/ln

Tear CD

Tear MDTear CD32 Grams34 Grams

Description Value

Basis Weight 40 Lbs/Rm

Caliper 2.5 Mil

Regulatory Approval

RoHSProp65REACHYesYesYes
TPCH
CPSIA
Yes
No

Direct Food

No

Last update: 05/01/2024

^{*}Please contact your sales representative for details

^{*}Please contact your sales representative for details

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS: Beontag 222 Mound Avenue Miamisburg, OH 45342

800-358-4448 orders.us@beontag.com