



Pressure-sensitive adhesives

Acrylic

Paper

# 8.5" X 11" ORANGE FLUORESCENT / PERMANENT / 80# SCOREBACK L-3

ITEM #SC-022

## Facestock

A premium coated one side face stock in a bright fluorescent color with outstanding ink receptivity and print characteristics. It also offers good flexibility and high internal strength for ease in converting.

### Type

Paper

### Tensile MD

26 Lbs/in

### Tensile CD

14 Lbs/in

### Tear MD

45 Grams

### Tear CD

53 Grams

Properties	Value
Caliper	3.80 Mil

## Regulatory Approval

RoHS	Prop65	REACH
Yes	Yes	Yes
TPCH	CPSIA	FSC
Yes	Yes	No

\*Please contact your sales representative for details

## Adhesive

A general purpose acrylic adhesive showing good initial tack with high shear and ultimate adhesion. It has good plasticizer, UV and solvent resistance. This adhesive displays excellent die-cutting and stripping characteristics and has good adhesion to many different substrates.

Composition	Type	Shear
Acrylic	Permanent	300
Application Temperature	Min. Application Temperature	Max. Application Temperature
35 F	-65 F	180 F

Properties	Value
Stainless Steel	5.2 lbs/linear in.
Glass	2.8

<b>Polyethylene</b>	2.9	
<b>Corrugated</b>	1.40 lbs./in.	
<b>Painted Metal</b>	5.2 lbs/linear in.	
<b>Loop Tack</b>	2.20 lbs./in2	
<b>Regulatory Approval</b>		
<b>RoHS</b> Yes	<b>Prop65</b> No	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>UL</b> No
<b>Direct Food</b> Yes	<b>Indirect Food</b> Yes	
*Please contact your sales representative for details		

<b>Liner</b> This liner is clay-coated bleached kraft designed for roll-to-sheet applications. It is manufactured with scores every 1.25\" apart.		
<b>Type</b> 9019084		
<b>Tensile MD</b> 36 Lbs/In	<b>Tensile CD</b> 21 Lbs/In	
<b>Tear MD</b> 61 Grams	<b>Tear CD</b> 71 Grams	
<b>Description</b>		
<b>Value</b>		
<b>Basis Weight</b>	72 Lbs/Rm	
<b>Caliper</b>	4.6 Mil	
<b>Regulatory Approval</b>		
<b>RoHS</b> Yes	<b>Prop65</b> Yes	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>UL</b> No
<b>Direct Food</b> No		
*Please contact your sales representative for details		

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages. BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products

have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

222 Mound Avenue Miamisburg, OH 45342

[800-358-4448](tel:800-358-4448)

[orders.us@beontag.com](mailto:orders.us@beontag.com)