

Pressure-sensitive adhesives

Acrylic Paper

## Bright Gold Laminated Foil / TS523 @ 1.5 Cwt. / 50#SCK L-3

ITEM #954

Facestock			
A 60# acrylic topcoated foil paper that accepts water base and solvent base inks and can be embossed.			
Туре			
Paper			
Tensile MD	Tensile CD		
36 Lbs/in	23 Lbs/in		
Tear MD	Tear CD		
50 Grams	51 Grams		
Properties	Value		
Caliper	3.60 Mil		
Regulatory Approval			
RoHS	Prop65	REACH	
Yes	Yes	Yes	
ТРСН	CPSIA	FSC	
Yes	Yes	No	
*Please contact your sales repr	resentative for details		

## Adhesive

A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.

<b>Type</b> Permanent	<b>Composition</b> Acrylic	<b>Shear</b> 300
<b>Application Temperature</b> 35 F	<b>Min. Application Temperature</b> -65 F	Max. Application Temperature 180 F
Properties	Value	
Properties Stainless Steel	<b>Value</b> 5.2 lbs/linear in.	

Polyethylene	2.9		
Corrugated	1.40 lbs./in.		
Painted Metal	5.2 lbs/linear in.		
Loop Tack	2.20 lbs./in2		
Regulatory Approval			
RoHS	Prop65	REACH	
<b>RoHS</b> Yes	<b>Prop65</b> No	<b>REACH</b> Yes	
	-		
Yes	No	Yes	
Yes TPCH	No	Yes UL	
Yes <b>TPCH</b> Yes	No <b>CPSIA</b> Yes	Yes UL	

## Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

<b>Type</b> 5517353			
Tensile MD	Tensile CD		
40 Lbs/In	24 Lbs/In		
Tear MD	Tear CD		
44 Grams	48 Grams		
Description	Value		
Basis Weight	50 Lbs/Rm		
Caliper	3.2 Mil		
<b>Regulatory Approval</b>			
RoHS	Prop65	REACH	
Yes	Yes	Yes	
ТРСН	CPSIA	UL	

ТРСН	CPSIA	UL	
Yes	Yes	No	
<b>Direct Food</b> No			
*Please contact your sales repre	sentative for details		

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag 6206 Wolf Creek Pike Trotwood, OH 45426 <u>800-358-4448</u> <u>orders.us@beontag.com</u>