

Pressure-sensitive adhesives

Acrylic

Paper

Bright Silver Metallized Paper / AT333 @ 1.30 Cwt. / 40#SCK L-3

ITEM #5805

Facestock

A bright silver paper facestock. A reflective, acrylic lacquer coated metallized paper facestock for excellent flexographic print results.

Type

Paper

Properties	Value
Caliper	2.60 Mil

Regulatory Approval

RoHS	Prop65	REACH
Yes	Yes	Yes
ТРСН	CPSIA	FSC
Yes	Yes	No

^{*}Please contact your sales representative for details

Adhesive

An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 F. Very good plasticizer, UV and solvent resistance. AT333 adhesive allows for short term reposition on many substrates, yet displays excellent permanency at room temps.

Composition Acrylic	Type Permanent	Shear 60
Application Temperature -20 F	Min. Application Temperature -65 F	Max. Application Temperature 160 F
Properties	Value	
Stainless Steel	4.7 lbs/linear in.	
Glass	1.3	
Polyethylene	2.2	
Corrugated	1.40 lbs./in.	
Painted Metal	4.4 lbs/linear in.	

Loop Tack	2.20 lbs./in.		
Regulatory Approval			
RoHS	Prop65	REACH	
Yes	No	Yes	
ТРСН	CPSIA	UL	
Yes	Yes	No	
Direct Food	Indirect Food		
No	Yes		

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

· · · · · · · · · · · · · · · · · · ·	t surface. Due to its high internal strength it will withstand all conventional process tting, butt cutting, line scoring and dispensing.	on ig
Type 5517342		
Tensile MD	Tensile CD	
34 Lbs/In	22 Lbs/In	
Tear MD	Tear CD	
32 Grams	34 Grams	
Description	Value	
Basis Weight	40 Lbs/Rm	
Caliper	2.5 Mil	
Regulatory Approval		

Regulatory Approval		
RoHS	Prop65	REACH
Yes	Yes	Yes
ТРСН	CPSIA	UL
Yes	Ves	No

Direct Food

No

*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

^{*}Please contact your sales representative for details

Beontag
222 Mound Avenue Miamisburg, OH 45342
800-358-4448
orders.us@beontag.com