



Pressure-sensitive adhesives

Acrylic

Paper

BRIGHT WHITE EDP / TP160 @ 1.3 Cwt. / 50#SCK L-3

ITEM #9009229

Facestock

A white uncoated litho designed with smudge resistance for high speed converting while having excellent perforating, punching and fanfolding characteristics. This stock also offers 88% in brightness and 83% opacity.

Type

Paper

Tensile MD

40 Lbs/in

Tensile CD

20 Lbs/in

Tear MD

45 Grams

Tensile CD

50 Grams

Properties

Value

Caliper

3.50 Mil

Opacity

85

Regulatory Approval

FSC

No

*Please contact your sales representative for details

Adhesive

An improved general purpose acrylic adhesive showing good initial tack, shear, and high ultimate adhesion. It has a good plasticizer, UV and solvent resistance, as well as compostability. This adhesive also displays excellent die-cutting and stripping traits & has excellent adhesion to many different substrates, with an application temperature of +25 °F.

Composition

Acrylic

Type

Permanent

Shear

79

Application Temperature

25 F

Min. Application Temperature

-65 F

Max. Application Temperature

200 F

Typical Adhesion values

Properties

Value

Stainless Steel

6.8 lbs/linear in.

Glass

0.0

Polyethylene

6.0

Corrugated	1.20 lbs./in.
Painted Metal	6.4 lbs/linear in.
Loop Tack	2.90 lbs./in.

Regulatory Approval

RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	Direct Food No
Indirect Food Yes		

*Please contact your sales representative for details

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type
5517353

Tensile MD 40 Lbs/In	Tensile CD 24 Lbs/In
Tear MD 44 Grams	Tensile CD 48 Grams

Description	Value
Basis Weight	50 Lbs/Rm
Caliper	3.2 Mil

Regulatory Approval

RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No		

*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at

BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

222 Mound Avenue Miamisburg, OH 45342

[800-358-4448](tel:800-358-4448)

orders.us@beontag.com