

BRIGHT WHITE EDP / TR440 @ 1.0 Cwt. / 3.4 MIL  
LAYFLAT L-3

ITEM #4491872

Facestock

A white uncoated litho designed with smudge resistance for high speed converting while having excellent perforating, punching and fanfolding characteristics. This stock also offers 88% in brightness and 83% opacity.

Type

Paper

Tensile MD

40 Lbs/in

Tensile CD

20 Lbs/in

Tear MD

45 Grams

Tear CD

50 Grams

Properties

Value

Caliper

3.50 Mil

Opacity

85

Brightness

88

Regulatory Approval

FSC

No

\*Please contact your sales representative for details

Adhesive

A specialty clear acrylic adhesive showing good initial removable tack with high shear and high removable adhesion. This adhesive has excellent clarity & minimum cold flow. Good removability on a wide range of substrates including corrugated and many plastic surfaces.

Type

Removable

Composition

Acrylic

Shear

110

Application Temperature

40 F

Min. Application Temperature

-65 F

Max. Application Temperature

150 F

Properties

Value

Stainless Steel

4.7 lbs/linear in.

<b>Glass</b>	3.0	
<b>Polyethylene</b>	1.4	
<b>Corrugated</b>	1.20 lbs./in.	
<b>Painted Metal</b>	4.2 lbs/linear in.	
<b>Loop Tack</b>	1.70 lbs./in.	
<b>Regulatory Approval</b>		
<b>RoHS</b> Yes	<b>Prop65</b> No	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>UL</b> No
<b>Direct Food</b> No	<b>Indirect Food</b> Yes	
*Please contact your sales representative for details		

<b>Liner</b> A bleached kraft liner which has been silicone coated one side to give a controlled release. It is designed to withstand die-cutting, marginal punching, perforating, fanfolding and refolding process while providing excellent dimensional stability.		
<b>Tensile MD</b> 35	<b>Tensile CD</b> 15	
<b>Tear MD</b> 50	<b>Tear CD</b> 75	
<b>Description</b>	<b>Value</b>	
<b>Basis Weight</b>	0	
<b>Caliper</b>	3,4	
<b>Regulatory Approval</b>		
<b>RoHS</b> Yes	<b>Prop65</b> Yes	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	
*Please contact your sales representative for details		

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages. BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:  
Beontag  
6206 Wolf Creek Pike  
Trotwood, OH 45426  
[800-358-4448](tel:800-358-4448)  
[orders.us@beontag.com](mailto:orders.us@beontag.com)