

FSC ScandCoat MC PB SSP 50N x 2 HG0 x 2



ITEM #F120000JOP000

Description

ScandCoat MC is a medium gloss machine coated paper with good whiteness. It is a versatile paper which is suitable for a very wide range of primary label work.

Developed for general colour printing, ScandCoat MC gives good colour lift and can be printed by flexography, rotary or flat-bed letterpress, offset lithography, screen process and can be foil blocked and varnished.

It can also be thermal transfer overprinted with suitable smudge resistant ribbons.

This is a PiggyBack construction that has two release coated backing papers, two layers of adhesive and a face material which allows a label to be applied, complete with backing, for future or further application.

The values indicated in this leaflet are not intended to be a specification but a guide to the values that may generally be expected. Customers should independently determine, prior to use, the suitability of any material for a specific purpose. All information is subject to change without notice.

Facestock

ScandCoat MC is a medium gloss machine coated paper with good whiteness. It is a versatile paper which is suitable for a very wide range of primary label work. Developed for general colour printing, ScandCoat MC gives good colour lift and can be printed by flexography, rotary or flat-bed letterpress, offset lithography, screen process and can be foil blocked and varnished. It can also be thermal transfer overprinted with suitable smudge resistant ribbons.

Type

Paper

Properties

Method

Value

Basis Weight

ISO 536

78 ± 3g/m²

Caliper

ISO 534

68 ± 5μ

Opacity

ISO 2471

89%

Regulatory Approval

FSC

Yes

*Please contact your sales representative for details

Adhesive

ScandStick Permanent 50N has excellent initial tack with high bond strength at elevated, room and chilled temperatures, as well as in moist conditions. It has been formulated to adhere to a wide variety of substrates, including corrugated cardboard, low surface energy materials like polyethylene and non-polar surfaces. SSP 50N provides enhanced conver-

sion characteristics, allowing die-cutting at higher speeds and is designed for both paper and synthetic face materials. Limitation: Not suitable for labelling plasticised PVC.

Composition Rubber	Type Permanent	Application Temperature -5 F
Min. Application Temperature -40 F	Max. Application Temperature 70 F	

Regulatory Approval

Food contact Meets composition requirement of indirect food additives regulation FDA175.105, BfR XIV.	FDA 21 CFR 175.105, BfR XIV Yes	ISEGA approved for direct contact with dry and moist non-fatty foods Yes
---	---	--

*Please contact your sales representative for details

Liner

HG0 honey glassine backing allows high speed conversion and consistent dispensing on a wide range of equipment.

Type
Paper

Description	Method	Value
Caliper	ISO 534	49 ± 3μ
Transparency	ISO 2469	50%

*Please contact your sales representative for details

Final product

ScandCoat MC is a medium gloss machine coated paper with good whiteness. It is a versatile paper which is suitable for a very wide range of primary label work.

Developed for general colour printing, ScandCoat MC gives good colour lift and can be printed by flexography, rotary or flat-bed letterpress, offset lithography, screen process and can be foil blocked and varnished.

It can also be thermal transfer overprinted with suitable smudge resistant ribbons.

This is a PiggyBack construction that has two release coated backing papers, two layers of adhesive and a face material which allows a label to be applied, complete with backing, for future or further application.

The values indicated in this leaflet are not intended to be a specification but a guide to the values that may generally be expected. Customers should independently determine, prior to use, the suitability of any material for a specific purpose. All information is subject to change without notice.

Format
Roll

Description	Value
Typical Caliper	182 ± 20μ

Regulatory Approval

Certificate

The product is registered to SCS-COC-004802 FSC™ Mix credit.

Material Shelf Life

12 months stored at 20°C/50% RH

*Please contact your sales representative for details

Last update: 05/01/2024

ADDRESS:

Beontag

Pål Anders väg 4, 263 35

Höganäs, Sweden

+46 42 25 00 50

orders.scandstick@beontag.com