

Pressure-sensitive adhesives

Acrylic

Paper

# ORANGE FLUORESCENT / TR440 @ 1.1 Cwt. / 40#SCK L-5

ITEM #96070

#### **Facestock**

A premium coated one side face stock in a bright fluorescent color with outstanding ink receptivity and print characteristics. It also offers good flexibility and high internal strength for ease in converting.

### **Type**

Paper

Tensile MD
26 Lbs/in
14 Lbs/in

Tear MD
45 Grams
53 Grams

Properties Value

Caliper 3.80 Mil

## **Regulatory Approval**

RoHSProp65REACHYesYesYes
TPCH
Yes
Yes
No

## **Adhesive**

A specialty clear acrylic adhesive showing good initial removable tack with high shear and high removable adhesion. This adhesive has excellent clarity & minimum cold flow. Good removability on a wide range of substrates including corrugated and many plastic surfaces.

| <b>Type</b><br>Removable            | <b>Composition</b> Acrylic                | <b>Shear</b><br>110                          |
|-------------------------------------|---|--|
| <b>Application Temperature</b> 40 F | <b>Min. Application Temperature</b> -65 F | <b>Max. Application Temperature</b><br>150 F |
| Properties                          | Value                                     |  |
| Stainless Steel                     | 4.7 lbs/linear in.                        |  |
| Glass                               | 3.0                                       |  |

<sup>\*</sup>Please contact your sales representative for details

Polyethylene 1.4

Corrugated 1.20 lbs./in.

Painted Metal 4.2 lbs/linear in.

**Loop Tack** 1.70 lbs./in.

### **Regulatory Approval**

RoHSProp65REACHYesNoYesTPCHCPSIAULYesYesNo

Direct Food Indirect Food

No Yes

\*Please contact your sales representative for details

## Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

| Tensile MD | Tensile CD |
|------------|------------|
|            |            |

34 22

Tear MD Tear CD 32 34

| Description  | Value |
|--------------|-------|
| Basis Weight | 40    |
| Caliper      | 2,5   |

## **Regulatory Approval**

RoHSProp65REACHYesYes

TPCH
Yes

CPSIA
Yes

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

<sup>\*</sup>Please contact your sales representative for details

6206 Wolf Creek Pike Trotwood, OH 45426 800-358-4448 orders.us@beontag.com