

ScandMet S SSP713 HG0

Description

ScandMet S is a bright silver metallised printing paper, that has been coated with a print receptive acrylic lacquer.

The material offers top print quality by all conventional print methods, like flexography, letterpress, offset and screen.

Note that special inks for non-absorbent materials should be used.

The values indicated in this leaflet are not intended to be a specification but a guide to the values that may generally be expected. Customers should independently determine, prior to use, the suitability of any material for a specific purpose. All information is subject to change without notice.

Facestock

ScandMet S is a bright silver metallised printing paper, that has been coated with a print receptive acrylic lacquer. The material offers top print quality by all conventional print methods, like flexography, letterpress, offset and screen. Note that special inks for non-absorbent materials should be used.

Type
Paper

Properties	Method	Value
Basis Weight	ISO 536	74 ± 3g/m²
Caliper	ISO 534	73 ± 5µ
Smoothness	ISO 5627	> 12900s

Regulatory Approval

FSC
No

*Please contact your sales representative for details

Adhesive

SSP713 has excellent initial tack and adhesion on a wide variety of substrates, including apolar, slightly rough and curved substrates. Particularly good adhesion to cardboard, plastic and glass. Note: Not advised for labelling highly plasticised materials, eg: flexible PVC

Composition	Type	Application Temperature
Rubber	Permanent	8 F
Min. Application Temperature	Max. Application Temperature	
-10 F	70 F	

Properties	Value	
Stainless Steel	18N	
Regulatory Approval		
Food contact	FDA 21 CFR 175.105, BfR XIV	ISEGA approved for direct contact with dry and moist non-fatty foods
Complies with FDA175.105, BfR XIV.	Yes	Yes
*Please contact your sales representative for details		

Liner		
HG0 honey glassine backing allows high speed conversion and consistent dispensing on a wide range of equipment.		
Description	Method	Value
Basis Weight	ISO 536	55 ± 3g/m²
Caliper	ISO 534	49 ± 3µ
Transparency	ISO 2469	50%
*Please contact your sales representative for details		

Final product	
Format	
Roll	
Description	Value
Typical Caliper	142 ± 10µ
Regulatory Approval	
Material Shelf Life	
12 months stored at 20°C/50% RH	
*Please contact your sales representative for details	

Last update: 05/01/2024

ADDRESS:
Beontag
Pål Anders väg 4, 263 35
Höganäs, Sweden
+46 42 25 00 50
orders.scandstick@beontag.com