

# TECHNI-GLOSS II HIGH GLOSS / IP400 @ 1.7 Cwt. / 44#PK L-4

ITEM #86575

### Facestock

A premium cast coated C1S white high gloss paper with a smooth print surface that offers excellent receptivity and print characteristics. The 90% gloss rating provides for the desired wet look label graphics that product manufacturers desire to enhance sales activity.

#### Type

Paper

#### Tensile MD

25 Lbs/in

#### Tensile CD

0 Lbs/in

#### Tear MD

35 Grams

#### Tear CD

40 Grams

Properties	Value
------------	-------

Caliper	3.70 Mil
Opacity	90
Brightness	87

### Regulatory Approval

RoHS	Prop65	REACH
------	--------	-------

Yes	Yes	Yes
TPCH	CPSIA	UL
Yes	Yes	No
FSC		
No		

\*Please contact your sales representative for details

### Adhesive

A specialty adhesive designed to adhere to glass wine bottles with good ultimate adhesion when applied at temperatures as low as +35 F. Excellent permanency at room temperatures. Good plasticizer, UV & solvent resistance. Excellent adhesive for wet strength wine label facestocks when submersed in ice buckets.

Composition	Type	Shear
-------------	------	-------

Acrylic	Permanent	80
Application Temperature	Min. Application Temperature	Max. Application Temperature

35 F	-65 F	200 F
Properties	Value	
Stainless Steel	5.5 lbs/linear in.	
Glass	3.2	
Polyethylene	2.0	
Corrugated	1.45 lbs./in.	
Painted Metal	3.0 lbs/linear in.	
Loop Tack	5.00 lbs./in.	
Regulatory Approval		
RoHS	Prop65	REACH
Yes	No	Yes
TPCH	CPSIA	UL
Yes	Yes	No
Direct Food	Indirect Food	
No	Yes	
*Please contact your sales representative for details		

Liner

A medium weight natural kraft coated 1 side (C1S) with a gloss polyethylene. Silicone coating has been added on the gloss side (C1S) for a controlled release. It has superb smoothness, excellent dimensional stability and exceptional layflat characteristics.

Type

17745

Tensile MD

35 Lbs/In

Tensile CD

13 Lbs/In

Tear MD

35 Grams

Tear CD

50 Grams

Description

Value

Basis Weight

44 Lbs/Rm

Caliper

3.2 Mil

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

UL

No

Direct Food

No

\*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

222 Mound Avenue Miamisburg, OH 45342

[800-358-4448](tel:800-358-4448)

[orders.us@beontag.com](mailto:orders.us@beontag.com)