

Pressure-sensitive adhesives

Acrylic

Paper

# TECHNI-THERM DIRECT NTC / AT333 @ 1.30 Cwt. / 40#SCK L-3

ITEM #881947

### **Facestock**

A medium sensitivity, non-topcoated direct thermal label facestock designed for short-duration applications in dry environments. This paper has an initial activation temperature of 185°F and an effective activation temperature of 280°F.

## **Type**

Paper

Tensile MD Tensile CD >21 11.5 lbs.in

Properties Value

Caliper 3.03 mil

# **Regulatory Approval**

RoHSProp65REACHYesYesYes
TPCH
CPSIA
Yes
No

FSC No

# **Adhesive**

An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 F. Very good plasticizer, UV and solvent resistance. AT333 adhesive allows for short term reposition on many substrates, yet displays excellent permanency at room temps.

<b>Type</b> Permanent	<b>Composition</b> Acrylic	<b>Shear</b> 60
<b>Application Temperature</b> -20 F	<b>Min. Application Temperature</b> -65 F	<b>Max. Application Temperature</b> 160 F
Properties	Value	
Stainless Steel	4.7 lbs/linear in.	
Glass	1.3	

<sup>\*</sup>Please contact your sales representative for details

Polyethylene 2.2

**Corrugated** 1.40 lbs./in.

Painted Metal 4.4 lbs/linear in.

**Loop Tack** 2.20 lbs./in.

# **Regulatory Approval**

RoHSProp65REACHYesNoYesTPCHCPSIAUL

Yes

Direct Food Indirect Food

No Yes

## Liner

Yes

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

No

No

#### **Type**

5517342

Tensile MDTensile CD34 Lbs/ln22 Lbs/ln

**Tear MD**32 Grams

Tear CD
34 Grams

**Description** Value

Caliper 2.5 Mil

# **Regulatory Approval**

RoHS<br/>YesProp65<br/>YesREACH<br/>YesTPCHCPSIAUL

Yes

40 Lbs/Rm

**Direct Food** 

**Basis Weight** 

No

Yes

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

<sup>\*</sup>Please contact your sales representative for details

<sup>\*</sup>Please contact your sales representative for details

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
800-358-4448
orders.us@beontag.com