



Pressure-sensitive adhesives

Acrylic

Paper

# TECHNI-THERM DIRECT RX / TR440 @ 1.0 Cwt./ 40#SCK L-3

ITEM #68695

## Facestock

An exceptional topcoated thermal label facestock specifically engineered for pharmacy prescription vial labels where superior image durability is required. The brightness of this Direct Thermal product is designed for dark images on pharmacy thermal printers.

### Type

Paper

### Tear MD

50 Grams

### Tear CD

83 Grams

### Properties

### Value

### Basis Weight

53

### Caliper

3.20 Mil

## Regulatory Approval

### RoHS

Yes

### Prop65

Yes

### REACH

Yes

### TPCH

Yes

### CPSIA

Yes

### FSC

No

\*Please contact your sales representative for details

## Adhesive

A specialty clear acrylic adhesive showing good initial removable tack with high shear and high removable adhesion. This adhesive has excellent clarity & minimum cold flow. Good removability on a wide range of substrates including corrugated and many plastic surfaces.

### Type

Removable

### Composition

Acrylic

### Shear

110

### Min. Application Temperature

40 F

### Min. Service Temperature

-65 F

### Max. Application Temperature

150 F

### Properties

### Value

### Stainless Steel

4.7 lbs/linear in.

### Glass

3lbs/linear in.

<b>Polyethylene</b>	1.4
<b>Corrugated</b>	1.20 lbs./in.
<b>Painted Metal</b>	4.2 lbs/linear in.
<b>Loop Tack</b>	1.70 oz/in <sup>2</sup>

### Regulatory Approval

<b>RoHS</b> Yes	<b>Prop65</b> Yes	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>Direct Food</b> No
<b>Indirect Food</b> Yes		

\*Please contact your sales representative for details

### Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

**Type**  
5517342

<b>Tensile MD</b> 34	<b>Tensile CD</b> 22
<b>Tear MD</b> 32	<b>Tear CD</b> 34

Description	Value
<b>Basis Weight</b>	40
<b>Caliper</b>	2.5

### Regulatory Approval

<b>RoHS</b> Yes	<b>Prop65</b> Yes	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>UL</b> No
<b>Direct Food</b> No		

\*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

6206 Wolf Creek Pike

Trotwood, OH 45426

[800-358-4448](tel:800-358-4448)

[orders.us@beontag.com](mailto:orders.us@beontag.com)