

Pressure-sensitive adhesives

Acrylic

Acrylic

Paper

TECHNI-THERM DIRECT WS / TP170 @ 1.3 Cwt. / 40#SCK L-3

ITEM #899103

Facestock

A top coated direct thermal face with initial activation temperature of 185 F and an effective activation temperature of 280 F. Techni-Therm Direct WS has excellent light stability to resist fading from UV light and superior curl control to insure layflat properties.

Type

Paper

Tensile MD
20 Lbs/in
13 Lbs/in

Tear MD
40 Grams
50 Grams

Value
3.20 Mil
85

Regulatory Approval

Brightness

RoHS	Prop65	REACH
Yes	Yes	Yes
TROLL		
TPCH	CPSIA	FSC

89

Adhesive

A general purpose acrylic adhesive showing good initial tack with high shear and high ultimate adhesion. It has good plasticizer, UV and solvent resistance. This adhesive displays excellent die-cutting and stripping characteristics and has good adhesion to many different substrates.

Composition Acrylic	Type Permanent	Shear 300
Application Temperature 35 F	Min. Application Temperature -65 F	Max. Application Temperature 180 F

^{*}Please contact your sales representative for details

Stainless Steel 5.2 lbs/linear in. Glass 3.2 Polyethylene 1.6 Corrugated 1.40 lbs./in. Painted Metal 5.2 lbs/linear Loop Tack 2.20 lbs./in2 Regulatory Approval RoHS Yes No TPCH CPSIA		
Polyethylene 1.6 Corrugated 1.40 lbs./in. Painted Metal 5.2 lbs/linear Loop Tack 2.20 lbs./in2 Regulatory Approval RoHS Yes Prop65 No CPSIA		
Corrugated 1.40 lbs./in. Painted Metal 5.2 lbs/linear Loop Tack 2.20 lbs./in2 Regulatory Approval RoHS Yes No TPCH CPSIA		
Painted Metal 5.2 lbs/linear Loop Tack 2.20 lbs./in2 Regulatory Approval RoHS Yes Prop65 No TPCH CPSIA		
Loop Tack2.20 lbs./in2Regulatory ApprovalProp65RoHSProp65YesNoTPCHCPSIA		
Regulatory Approval RoHS Prop65 Yes No TPCH CPSIA		
RoHS Yes No CPSIA		
Yes No CPSIA		
TPCH CPSIA	REACH	
	Yes	
	UL	
Yes	No	
Direct Food Indirect Food		
No Yes		

Adhesive

*Please contact your sales representative for details

A general purpose patterned acrylic adhesive showing good initial tack with high shear and high ultimate adhesion. It has good plasticizer, UV and solvent resistance. This adhesive displays excellent die-cutting and stripping characteristics and has good adhesion to many different substrates.

Composition Acrylic	Type Permanent	Shear 300
Application Temperature 35 F	Min. Application Temperature -65 F	Max. Application Temperature 180 F
Properties	Value	
Stainless Steel	5.2 lbs/linear in.	
Glass	3.2	
Polyethylene	1.6	
Corrugated	1.40 lbs./in.	
Painted Metal	5.2 lbs/linear	
Loop Tack	2.20 lbs./in2	
Regulatory Approval		
RoHS	Prop65	REACH
Yes	No	Yes
ТРСН	CPSIA	UL
Yes	Yes	No
Direct Food	Indirect Food	

No Yes

*Please contact your sales representative for details

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type

5517342

Tensile MDTensile CD34 Lbs/ln22 Lbs/ln

Tear MD32 Grams

Tear CD
34 Grams

Description	Value
Basis Weight	40 Lbs/Rm
Caliper	2.5 Mil

Regulatory Approval

RoHS	Prop65	REACH
Yes	Yes	Yes
TPCH	CPSIA	UL
Yes	Yes	No

Direct Food

No

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

222 Mound Avenue Miamisburg, OH 45342

800-358-4448

orders.us@beontag.com

^{*}Please contact your sales representative for details