



Pressure-sensitive adhesives

Acrylic

Acrylic

Paper

TECHNI-THERM DIRECT WS / TR440 @ 1.0 Cwt. / 40#SCK L-3

ITEM #889348

Facestock

A top coated direct thermal face with initial activation temperature of 185 F and an effective activation temperature of 280 F. Techni-Therm Direct WS has excellent light stability to resist fading from UV light and superior curl control to insure layflat properties.

Type

Paper

Tensile MD

20 Lbs/in

Tensile CD

13 Lbs/in

Tear MD

40 Grams

Tear CD

50 Grams

Properties	Value
------------	-------

Basis Weight	53 # Rm 25 x 38
Caliper	3.20 Mil
Opacity	85
Brightness	89

Regulatory Approval

RoHS	Prop65	REACH
------	--------	-------

Yes	Yes	Yes
TPCH	CPSIA	FSC
Yes	Yes	No

*Please contact your sales representative for details

Adhesive

A specialty clear acrylic adhesive showing good initial removable tack with high shear and high removable adhesion. This adhesive has excellent clarity & minimum cold flow. Good removability on a wide range of substrates including corrugated and many plastic surfaces.

Type	Composition	Shear
------	-------------	-------

Removable	Acrylic	110
Application Temperature	Min. Application Temperature	Max. Application Temperature
40 F	-65 F	150 F

Properties	Value	
Stainless Steel	4.7 lbs/linear in.	
Glass	3.0	
Polyethylene	1.4	
Corrugated	1.20 lbs./in.	
Painted Metal	4.2 lbs/linear in.	
Loop Tack	1.70 lbs./in.	
Regulatory Approval		
RoHS	Prop65	REACH
Yes	No	Yes
TPCH	CPSIA	UL
Yes	Yes	No
Direct Food	Indirect Food	
No	Yes	
*Please contact your sales representative for details		

Adhesive		
A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.		
Type	Composition	Shear
Permanent	Acrylic	110
Application Temperature	Min. Application Temperature	Max. Application Temperature
35 F	-65 F	180 F
Properties	Value	
Stainless Steel	4.7 lbs/linear in.	
Glass	2.8	
Polyethylene	2.9	
Corrugated	1.20 lbs./in.	
Painted Metal	4.2 lbs/linear in.	
Loop Tack	1.70 lbs./in.	
Regulatory Approval		
RoHS	Prop65	REACH
Yes	No	Yes
TPCH	CPSIA	UL

Yes	Yes	No
Direct Food	Indirect Food	
No	Yes	
*Please contact your sales representative for details		

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type

17142

Tensile MD

34 Lbs/In

Tensile CD

22 Lbs/In

Tear MD

32 Grams

Tear CD

34 Grams

Description

Value

Basis Weight

40 Lbs/Rm

Caliper

2.5 Mil

Regulatory Approval

RoHS

Yes

TPCH

Yes

Direct Food

No

Prop65

Yes

CPSIA

Yes

REACH

Yes

UL

No

*Please contact your sales representative for details

Liner Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.		
Type 5517342		
Tensile MD 34 Lbs/In	Tensile CD 22 Lbs/In	
Tear MD 32 Grams	Tear CD 34 Grams	
Description	Value	
Basis Weight	40 Lbs/Rm	

Caliper		2.5 Mil	
Regulatory Approval			
RoHS	Prop65	REACH	
Yes	Yes	Yes	
TPCH	CPSIA	UL	
Yes	Yes	No	
Direct Food			
No			
*Please contact your sales representative for details			

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
[800-358-4448](tel:800-358-4448)
orders.us@beontag.com