

TECHNI-THERM III / GP550 @ 1.3 Cwt. / 40#SCK L-3

ITEM #77329

Facestock

A coated one side thermal transfer facestock with outstanding ink receptivity and print characteristics. It also offers good flexibility and high internal strength for ease in converting. This facestock also offers a 90% brightness and an 82% opacity.

Type

Paper

Tensile MD

25 Lbs/in

Tensile CD

16 Lbs/in

Tear MD

34 Grams

Tensile CD

36 Grams

Properties

Value

Caliper

2.65 Mil

Opacity

8,2

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

UL

No

FSC

No

*Please contact your sales representative for details

Adhesive

A general purpose permanent acrylic with good initial tack and high ultimate adhesion. This adhesive is available on Thermal Transfer and Direct Thermal NTC paper face stocks, and displays excellent adhesion to most substrates where thermal transfer and non-topcoated direct thermal paper labels are typically utilized.

Composition

Acrylic

Type

Permanent

Shear

100

Application Temperature

-20 F

Min. Application Temperature

-65 F

Max. Application Temperature

200 F

Typical Adhesion values

Properties	Value
Stainless Steel	4.8 lbs/linear in.
Glass	4.0
Polyethylene	3.0
Corrugated	1.50 lbs./in.
Loop Tack	2.90 lbs./in.

Regulatory Approval		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	Direct Food No
Indirect Food Yes		

*Please contact your sales representative for details

Liner		
Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.		
Type 5517342		
Tensile MD 34 Lbs/In	Tensile CD 22 Lbs/In	
Tear MD 32 Grams	Tensile CD 34 Grams	

Description	Value
Basis Weight	40 Lbs/Rm
Caliper	2.5 Mil

Regulatory Approval		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No		

*Please contact your sales representative for details

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

222 Mound Avenue Miamisburg, OH 45342

[800-358-4448](tel:800-358-4448)

orders.us@beontag.com