

Pressure-sensitive adhesives

Acrylic

Acrylic

TECHNI-THERM III / TP170 @ 1.3 Cwt. / 50#SCK L-3 / TP170 @ 1.3 Cwt. / 50#SCK L-5

ITEM #799323

Facestock

A coated one side thermal transfer facestock with outstanding ink receptivity and print characteristics. It also offers good flexibility and high internal strength for ease in converting. This facestock also offers a 90% brightness and an 82% opacity.

Type

Paper

Tensile MD Tensile CD 25 Lbs/in 16 Lbs/in **Tear MD Tensile CD** 34 Grams 36 Grams

Properties Value 2.65 Mil Caliper

Opacity 8,2

Regulatory Approval

RoHS REACH Prop65 Yes Yes Yes **TPCH CPSIA** UL Yes Yes No

FSC No

*Please contact your sales representative for details

Adhesive

A general purpose acrylic adhesive showing good initial tack with high shear and high ultimate adhesion. It has good plasticizer, UV and solvent resistance. This adhesive displays excellent die-cutting and stripping characteristics and has good adhesion to many different substrates.

Composition	Туре	Shear
Acrylic	Permanent	300

Application Temperature Min. Application Temperature Max. Application Temperature -65 F 35 F 180 F

Typical Adhesion values Properties	Value	
Stainless Steel	5.2 lbs/linear in.	
Glass	3.0	
Polyethylene	1.0	
Corrugated	1.40 lbs./in.	
Painted Metal	5.2 lbs/linear in.	
Loop Tack	2.20 lbs./in.	
Regulatory Approval		
RoHS	Prop65	REACH
Yes	Yes	Yes
ТРСН	CPSIA	Direct Food
Yes	Yes	No
Indirect Food Yes		

Adhesive

TPCH Yes

*Please contact your sales representative for details

A general purpose patterned acrylic adhesive showing good initial tack with high shear and high ultimate adhesion. It has good plasticizer, UV and solvent resistance. This adhesive displays excellent die-cutting and stripping characteristics and has good adhesion to many different substrates.

and has good adhesion to many different substrates.			
Composition Acrylic	Type Permanent	Application Temperature 35 F	
Min. Application Temperature -65 F	Max. Application Temperature 180 F		
Typical Adhesion values Properties	Value		
Stainless Steel	5.2 lbs/linear in.		
Glass	3.0		
Polyethylene	1.0		
Painted Metal	5.2 lbs/linear in.		
Regulatory Approval			
RoHS Yes	Prop65 Yes	REACH Yes	

Direct Food

No

CPSIA

Yes

Indirect Food

Yes

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type

5517353

Tensile MD

40 Lbs/ln

24 Lbs/ln

Tear MD

44 Grams

48 Grams

Description	Value
Basis Weight	50 Lbs/Rm
Caliper	3.2 Mil

Regulatory Approval

RoHS	Prop65	REACH
Yes	Yes	Yes
ТРСН	CPSIA	UL
Yes	Yes	No

Direct Food

No

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Tensile MD 37	Tensile CD 20	
Tear MD 45	Tensile CD 53	
Description	Value	
Basis Weight	0	

^{*}Please contact your sales representative for details

^{*}Please contact your sales representative for details

Regulatory Approval			
RoHS	Prop65	REACH	
Yes	Yes	Yes	
ТРСН	CPSIA		
Yes	Yes		
*Please contact your sales representative for details			

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
222 Mound Avenue Miamisburg, OH 45342
800-358-4448
orders.us@beontag.com