



Pressure-sensitive adhesives

Hot Melt

Hot Melt

Paper

# TECHNI-THERM SP / AP151 @ 1.3 Cwt. / 40#SCK L-5

ITEM #73087

## Facestock

A coated one side thermal transfer facestock with outstanding ink receptivity and print characteristics. It also offers good flexibility and high internal strength for ease in converting. This facestock also offers an 86% brightness and an 87% opacity.

### Type

Paper

### Tensile MD

26 Lbs/in

### Tensile CD

18 Lbs/in

### Tear MD

42 Grams

### Tear CD

42 Grams

Properties	Value
Caliper	2.70 Mil
Opacity	87
Brightness	86

## Regulatory Approval

RoHS	Prop65	REACH
Yes	Yes	Yes
TPCH	CPSIA	UL
Yes	Yes	No
FSC		
No		

\*Please contact your sales representative for details

## Adhesive

An improved general purpose permanent rubber based adhesive which has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting & stripping traits.

Composition	Type	Shear
Hot Melt	Permanent	80
Application Temperature	Min. Application Temperature	Max. Application Temperature
35 F	-65 F	220 F

Properties	Value	
Stainless Steel	7.3 lbs/linear in.	
Glass	5.7	
Polyethylene	6.5	
Corrugated	2.50 lbs./in.	
Painted Metal	7.0 lbs/linear in.	
Loop Tack	5.00 lbs./in.	
Regulatory Approval		
RoHS	Prop65	REACH
Yes	No	Yes
TPCH	CPSIA	UL
Yes	Yes	No
Direct Food	Indirect Food	
No	Yes	
*Please contact your sales representative for details		

Adhesive		
An outstanding general purpose permanent opaque adhesive that has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting and stripping traits. Provides opacity for cover up applications.		
Composition	Type	Shear
Hot Melt	Permanent	80
Application Temperature	Min. Application Temperature	Max. Application Temperature
35 F	-65 F	220 F
Properties	Value	
Stainless Steel	7.3 lbs/linear in.	
Glass	5.7	
Polyethylene	6.5	
Corrugated	2.50 lbs./in.	
Painted Metal	7.0 lbs/linear in.	
Loop Tack	5.00 lbs./in.	
Regulatory Approval		
RoHS	Prop65	REACH
Yes	No	Yes
TPCH	CPSIA	UL

Yes	Yes	No
<b>Direct Food</b>	<b>Indirect Food</b>	
No	Yes	
*Please contact your sales representative for details		

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

<div>Tensile MD</div> <div>34</div>	<div>Tensile CD</div> <div>22</div>
<div>Tear MD</div> <div>32</div>	<div>Tear CD</div> <div>34</div>

Description	Value
Basis Weight	40
Caliper	2,5

Regulatory Approval

<div>RoHS</div> <div>Yes</div>	<div>Prop65</div> <div>Yes</div>	<div>REACH</div> <div>Yes</div>
<div>TPCH</div> <div>Yes</div>	<div>CPSIA</div> <div>Yes</div>	

\*Please contact your sales representative for details

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type

5517353

Tensile MD

40 Lbs/In

Tensile CD

24 Lbs/In

Tear MD

44 Grams

Tear CD

48 Grams

Description

Value

Basis Weight

50 Lbs/Rm

Caliper

3.2 Mil

Regulatory Approval

<b>RoHS</b>	<b>Prop65</b>	<b>REACH</b>
Yes	Yes	Yes
<b>TPCH</b>	<b>CPSIA</b>	<b>UL</b>
Yes	Yes	No
<b>Direct Food</b>		
No		
*Please contact your sales representative for details		

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:  
Beontag  
222 Mound Avenue Miamisburg, OH 45342  
[800-358-4448](tel:800-358-4448)  
[orders.us@beontag.com](mailto:orders.us@beontag.com)